

APP modified bituminous membrane - Slated

GENERAL

Biplas SL is a high performance waterproofing membrane especially formulated with reflective natural or color slates to give maximum protection against UV radiation in an exposed system application.

The presence of the slates will also provide an aesthetically pleasant surface. It is an ideal membrane re-roofing applications where it can be placed on top of the existing surface, providing an economical and efficient solution to leaking roofs.

Biplas.SL membrane is resistant to water-borne chemical attack.

COATING MIXTURE

The coating compound mix of **Biplas SL** membrane is produced with high quality bitumen modified with selected (APP) polymers and thermoplastic resins and stabilizers. This mixture gives the membrane its excellent resistance to atmospheric agents and thermal ageing. The mix also allows constant flexibility and plasticity at low or high temperatures. The compound also allows for quick application and torching.

SELF PROTECTING SHIELD

During the manufacturing process the upper surface of the membrane is uniformly coated with a layer of natural slate flakes (chips/granules) that adhere to the top surface of the membrane at high temperature. During this process the selvedge of the slated surface is left uncoated and 10 cm covered with a flammable film that can be torched, thus providing continuity at the overlaps and a perfect watertight seal.

The slate flakes provide protection for the waterproofing covering from ageing caused by infra red and UV rays. The reflective power of the natural slate also lowers the temperature underneath. The slate flakes may come in a variety of colors.

REINFORCEMENT CORE

Biplas SL membranes are reinforced with a 180 g/m² non woven spun bond polyester core. The core is of continuous thread, rot-proof material which has a high tensile strength and offers high resistance to tear and puncturing loads and remains highly flexible at temperatures below 0°C.

APPLICATION TOOLS & EQUIPMENT

The tools and equipment required to apply biplas membrane include a propane gas torch with related cylinder, a knife for cutting and trimming, a trowel with a rounded end.



PACKAGING

Leb	Syria	Jordan	UAE	Qatar	Kuwait	KSA	Oman
1x10 m	1x10 m	1x10 m	1x10 m	1x10 m	1x10 m	1x10 m	1x10 m

METHOD OF APPLICATION

The application of **Biplas SL** is both easy and quick. Where it is to be laid directly in a one-layer system on concrete, tiles or an existing roofing system, a coat of **weberdry prime WB** or **weberdry prime SB** at the rate of 200-300 g/m² should first be applied. Allow this coating to dry thoroughly. In areas of high humidity we recommend it should be left overnight.

As in all other application, the membrane should first be unrolled and positioned correctly on the surface to be treated. Each roll should overlap the adjacent roll by the size of the selvedge, i.e. 10 cm. Once the roll has been positioned correctly, the membrane should be rolled up again, taking care not to change its orientation. Using left to right movements, heat the lower surface of the membrane with a propane gas torch. This will cause slight surface melting and adhesion to the substrate. Continue the above method for consecutive rolls remembering overlaps must always cover the whole selvedge and end laps to

Properties	Test Method	TOLERANCE	Typical Values
Thickness	ASTM D5147 EN 1849-1	-0.2mm	4.00mm
Reinforcement base			180 gms/m ² non woven Polyester
Tensile strength - long - trans	EN 12311-1 EN 12311-1	20% ±20%	750 N/5cm 550 N/5cm
Elongation - long - trans	EN 12311-1 EN 12311-1	±15% ±15%	40% 45%
Lap joint strength - long - trans	EN 12317-1 EN 12317-1	±20% ±20%	750 N/5cm 550 N/5cm
TEAR RESISTANCE - long - trans	ASTM D5147 ASTM D5147	min min	550 N 375 N
Low temperature flexibility*		min	0° C
Puncture Resistance Static	EN 12730	min	20 kg
Puncture Resistance Dynamic	EN 12691	mlv	> 700mm
Water Absorption (n/a slate)	ASTM D570	mlv	<0.15%
Flow Resistance less than 2mm	EN1110	mlv	100°C
Reaction to fire	EN 13501-1	Euroclass	F
Biplas membranes are resistant to chlorides, sulphates and phosphates found in ground water.			

* Different cold flexibility value can be supplied to special order

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

NOTE

The information included on this Technical Data Sheet is the sole property of Saint-Gobain Middle East Holding SAL (previously SODAMCO Holding). The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

PG:29