

## Fast setting cementitious self-leveling floor for thickness from 2 to 15 mm

### PRODUCT

**weberfloor 515 PSC** is a floor overlay cementitious base single component product, used internally for levelling and smoothing differences in thicknesses from 2 to 15 mm, on new or existing substrates in order to receive all kinds of flooring covering. It has good abrasion resistance and provides a fast setting tough surface that will accept light traffic in less than 12hours with a good resistance to loads and traffic.

### SCOPE OF USE

**weberfloor 515 PSC** is used for internal application and specially designed to be applied as self-leveling prior the laying of resilient floors such as PVC, Vinyl, rubber, carpets as well as wood flooring, ceramics, or natural stones. It can be used in many areas such as:

- Hotels, theaters, hospitals, schools
- Industries, airports halls.

**weberfloor 515 PSC** can be used also for levelling existing concrete pavements, terrazzo, ceramic, or natural stone after a good surface preparation and priming. It could be applied over light weight screed.

**weberfloor 515 PSC** could be used with underfloor heating system according to special instructions respecting the start-up heating procedure.

### ADVANTAGES

- Highly fluid and easily workable.
- Good self levelling capacity.
- Fast setting ready for foot traffic in less than 12h depending on site condition.
- Smooth finishing.
- Good bond with reduced shrinkage.
- Low VOC.

### CHARACTERISTICS

Color	Grey Powder	
Grain size	< 1 mm	
Powder density	1.4	
Flowability test (mm) - EN 12706:1999	0 min	14 (mm)
	5 min	12.5 (mm)
	10 min	9.0 (mm)
Abrasion resistance EN 12808	Less than 310 (mm <sup>3</sup> )	
Setting time	≥ 3 hrs	
Pot life around	30 min.	
	depending on temperature substrate and site conditions	



### PACKAGING

Leb	Syria	Jordan	UAE	Qatar	Kuwait	KSA	Oman
25 kg	25 kg	-	-	-	-	-	-

Application temperature range	from +5°C to +30°C
Flexural strength at 28 days EN 13813:2003	7 (N/mm <sup>2</sup> )
Compressive strength at 28 days EN 13813:2003	35 (N/mm <sup>2</sup> )
VOC and formaldehyde content ISO/FDIS 11890-2/GC-MS	None (<10µg/l)

\*Results obtained at 17% water for Lebanon.

\*Properties listed above are only based on controlled laboratory samples and tests: Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

### APPLICABLE STANDARDS

EN 13813 CT,  
EN 12808,  
EN 12706:1999

### INSTRUCTIONS FOR USE

#### SUBSTRATE PREPARATION

- Concrete substrate should be at least 3 months old and structurally stable. (residual moisture <4% or internal relative humidity <90%)

- Concrete must be crack free. Thus, any crack must be repaired prior to application.
- All surfaces should be clean, dry, and free from grease, laitance, oil, dust, paint and any other substance that may prevent or reduce adhesion.
- Remove all weak, loose, smooth or broken pieces of concrete, until reaching a sound rough concrete. This can be achieved primarily by shot-blasting otherwise by medium scarifying or grinding.
- The prepared surface must have an average "surface tensile adhesion strength" greater than 1 MPa. Moreover, it should have CSP (concrete surface profile) of 3 to 5.
- Then, the substrate must be vacuumed, and primed with **weberfloor 4716**. Weber does not warrant any defect due to concrete substrate movement.

#### PRIMER APPLICATION

- **weberfloor 4716** must be brushed into the substrate using soft brush. Primer's puddles should be avoided.
- **weberfloor 4716** must be applied on one or two coats depending on the substrate
- For dry and porous substrate, dilute first coat of **weberfloor 4716** with water at the ratio 1:5. Allow to dry a clear film before applying the second layer with a dilution ratio 1:3
- For dense concrete, apply one coat of **weberfloor 4716** diluted at the ratio 1:3
- **weberfloor 515 PSC** should be applied as soon as the colour of the primed surface change from white to clear. For thicknesses higher than 10mm, it is recommended to fix soft strips as a separation between the walls (or columns) and the self-leveling before proceeding with the application.

#### PRODUCT PREPARATION

**weberfloor 515 PSC** is to be mixed in full bag batches. Do not mix partial bags. In Lebanon, each 25 Kg bag of **weberfloor 515 PSC** is to be mixed with 4.25 liters of clean and cool water. Measure and add the proper amount of water for each bag into a mixing container. Using a paddle type mixer on a slow speed drill, place the paddle in the mixing water and start the drill. Slowly add the **weberfloor 515 PSC** powder. Mix for a minimum of 2 minutes until lump free. Scrape the sides of the mixing container and remix for 1 minute. The mixed material should be lump free.

The mixed material should be lumps free Make sure that the mixed material has a temperature not exceeding 30°C (use ice if necessary to cool down water).

It is recommended to fix soft strips as a separation between the walls (or columns) and the self-leveling before proceeding with the application at thicknesses greater than 10 mm.

**Note: Do not add more water to a mix which has already begun to set.**

#### PRODUCT APPLICATION

Limit the work areas into manageable sections of approximately 20 m<sup>2</sup>. Reduce the width of the work area when applying in warmer temperatures. Pour the mixed material onto the prepared surface, then immediately spread it with a large metal trowel or spiked roller to aid in leveling and smoothing the surface. Do not walk in the wet material unless wearing spiked shoes or boots. Always keep a wet edge of material to pour fresh material into. Protect the material from wind when installing. Allow longer cure time of the material before walking on if the temperature is below 21°C.

**Weberfloor 515 PSC** can be used as part of floor heating application.

It is recommended to raise the temperature gradually when starting the heating process after the applied product is totally dried and set.

For more technical details, kindly consult our technical department.

**weberfloor 515 PSC** can be covered (vinyl, carpet, tiles,...) after 3 days from the application.

#### PRECAUTIONS

It is preferable to subdivide the total area of application in smaller ones not exceeding 20 m<sup>2</sup> each in order to facilitate the application of **weberfloor 515 PSC**. A soft frame should be fixed so when they finish the first section, you should remove the soft frame and apply the other section without leaving any joint between the 2 sections. All existing movement/expansion joints in the base should be maintained and continued through the **weberfloor 515 PSC**.

- In case of corridors, it is recommend it to fix control joints on each 15 linear meters and in each connection between corridor and room. The joints should be sealed with **weber jointseal PU**.

- In hot and humid weather, it is preferable to apply the product early morning or late afternoon.

- outside the recommended temperature range (higher than 35 deg.), please refer to the technical department for more details about the thickness and the method of application.

- Avoid work under heavy windy condition in which case the product may dry fast and cracks might appear. It is preferable to cover the working area with plastic sheets as soon as the surface is walkable.

- All the opening ( windows, doors) should be closed in order to reduce the effect of wind during the application and while the applied area still fresh. Any applied materials should be

protected from sun light.

- The surface is suitable for light foot traffic after 24 hours. However, avoid dragging heavy objects on it in order to avoid damaging the finished surface.
- After usage, clean tools with water.
- Depending on thickness, moisture content of self levelling and substrate, and the moisture sensitivity of the covering, wait 3 days minimum before covering the floor with carpeting, tiles, etc.
- For additional information, please consult our Technical Data Sheet or contact one of our Sales Engineers.

## CLEANING

Tools and equipment should be cleaned with water immediately after use.

## CONSUMPTION AND COVERAGE

1.7 kg/m<sup>2</sup>/mm thickness.

## STORAGE

One year after manufacturing date in its original packing non open and in dry cool area.

## SAFETY PRECAUTIONS

The product contains very fine powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable to do the application in a well ventilated area, to wear protective gear for hands, eyes and respiratory system and to avoid dust inhaling. Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting. In both cases seek medical attention. The product is non-flammable.

## DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

## NOTE

The information included on this Technical Data Sheet is the sole property of Saint-Gobain Middle East Holding SAL

(previously SODAMCO Holding). The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.