

Portland cement plaster

PRODUCT

weberpremix SP-2 is a cementitious ready mix plaster used for traditional plastering works in a clean and speedy manner, while keeping a homogeneous mix. Due to its high content in additives, it allows better shrinkage control as well as improved workability and curing.

weberpremix SP-2 is recommended for external and internal plastering on block walls, ceilings, concrete surfaces, bricks and for general filling up.

weberpremix SP-2 can be applied traditionally by hand or by using modern plaster-spraying machines. It should not be used on painted surfaces or floors.

For the application on Light Weight concrete blocks, it is recommended to use **weberpremix SP-3 FL** which is reinforced with polypropylene fibers.

CHARACTERISTICS

Colour	Grey
Composition	Portland cement, selected sand, specific additives.
Mixing ratio	8-9 liters per 50 kg bag
Powder density	1.55 ± 0.1
Wet mix life	> 2 hours at 200 °C
Resistance to fire as per BS EN 998 -1	Class A1

APPLICABLE STANDARDS

BS 5262: 1991
BS 5492: 1990
BS 4551: Part 2: 1998
ASTM C 150
ASTM C 926

INSTRUCTIONS FOR USE

SURFACE PREPARATION

The substrate must be clean, sound, and free from dust and all traces of oil and laitance.

A spatter dash slurry coat (**weberpremix SRC-1**, **SRC-2** or **SRC-S**) should be applied as a key coat for improved bonding & adhesion of subsequent layers.

A few hours before the application of **weberpremix SP-2**, dampen the rush coat with clean water.

PRODUCT PREPARATION

Mix manually using an electrical hand mixer or mechanically



PACKAGING

Leb	Syria	Jordan	UAE	Qatar	Kuwait	KSA	Oman
50 kg	50 kg	50 kg	50 kg	50 kg	50 kg	50 kg	50 kg

a 50 kg of **weberpremix SP-2** with 8 to 9 litres of clean water until a homogeneous paste is obtained. Let the mix rest for a few minutes.

If a spraying machine is used, the mixing is carried out automatically.

PRODUCT APPLICATION

Apply the plaster on the prepared surface by spraying it or manually with a plastering trowel at a thickness between 10 and 15 mm in one layer.

After levelling, finish the surface with a steel float or synthetic sponge as required.

Let the product set properly on the surface before any curing.

If more thickness is required, the application should be done in two layers. The 1st layer should be roughened then cured. The 2nd layer should be applied at least 48 hrs after the 1st one.

CURING

Protect the newly applied plaster from sunshine and wind.

The new plaster has to be cured with water for at least three days by spraying 3 to 4 times daily.

CONSUMPTION

Approximately 1.6 kg per m² per 1 mm thickness.

STORAGE

12 months after manufacturing date in original and non-open packaging, under cover, in dry condition, away from humidity, protected from extreme temperatures and direct sunlight.

SAFETY PRECAUTIONS

The product contains cement powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated area, and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting, in both cases seek medical attention. The product is non-flammable.

DISCLAIMER

The product contains cement powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated area, and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting, in both cases seek medical attention. The product is non-flammable.

NOTE

The information included on this Technical Data Sheet is the sole property of SODAMCO Holding. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

PG: 30

*Available only in GCC