

## Ready mixed spatterdash slurry coat for blocks

### PRODUCT

**weberpremix SRC-1** is a ready mixed mortar based on mineral bonding agent used for preparing surfaces before the rendering. It improves the adhesion of the new plaster, cement & gypsum based. It is applied on masonry blocks.

### Recommended rush-coats according to substrate

SUBSTRATE	PRODUCT
Regular Blocks	<b>weberpremix SRC-1</b>
Light-Weight Blocks	<b>weberpremix SRC-LW</b>
Fair faced Concrete	<b>weberpremix SRC-2</b>
Concrete with SCMs	<b>weberpremix SRC-S</b>

### CHARACTERISTICS

Appearance	Grey granular powder
Composition	Portland cement, selected sand, additives
Grain size	0 to 3 mm
Bulk density	1.5 ± 0.1
Wet density	2 ± 0.1
VOC and formaldehyde content ISO/FDIS 11890-2/GC-MS	None (<10µg/l)
Resistance to fire as per BS EN 998 -1	Class A1

### APPLICABLE STANDARDS

BS 5262: 1991  
BS 5492: 1990  
BS 4551: Part 2: 1998  
ASTM C 150  
ASTM C 926  
ASTM C 897

### INSTRUCTIONS FOR USE

#### SURFACE PREPARATION

Substrates must be sound, clean, dust free and free from all traces of oil, curing compound, gypsum, paint or laitance. The support must be dampened a few hours before the application of **weberpremix SRC-1**.

#### PRODUCT PREPARATION

Mix a 50 kg bag with 9 to 11 liters of potable cool water in order to obtain the consistency desired. Mixing has to be done with an electric mixer.



### PACKAGING

Leb	Syria	Jordan	UAE	Qatar	Kuwait	KSA	Oman
50 kg	50 kg	50 kg	50 kg	50 kg	50 kg	50 kg	50 kg

### PRODUCT APPLICATION

Apply the **weberpremix SRC-1** using a tyrolean box or a power spray gun.

### CURING

Protect the newly applied plaster from sunshine and wind. The new plaster has to be cured with water for at least three days by spraying 3 to 4 times daily.

### CONSUMPTION

Around 4 kg/m<sup>2</sup>, depending on the substrate and the application method.

### STORAGE

12 months after manufacturing date in original and non-open packaging, under cover, in dry condition, away from humidity, protected from extreme temperatures and direct sunlight.

### SAFETY PRECAUTIONS

The product contains cement powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated area, and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash

thoroughly with clean water. If swallowed, do not induce vomiting, in both cases seek medical attention. The product is non-flammable.

## DISCLAIMER

The product contains cement powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated area, and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting, in both cases seek medical attention. The product is non-flammable.

## NOTE

The information included on this Technical Data Sheet is the sole property of SODAMCO Holding. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

PG: 30

\*Available only in GCC