

Ready mixed spatterdash slurry coat for light weight blocks (Autoclaved Aerated Concrete Blocks)

PRODUCT

weberpremix SRC-LW is a ready mixed mortar based on mineral bonding agent used for preparing surfaces before the rendering. It improves the adhesion of the new plaster, cement & gypsum based. It is applied on light weight blocks.

Recommended rush-coats according to substrate

SUBSTRATE	PRODUCT
Regular Blocks	weberpremix SRC-1
Light-Weight Blocks	weberpremix SRC-LW
Concrete	weberpremix SRC-2
Concrete with SCMs	weberpremix SRC-S

CHARACTERISTICS

Appearance	Pinkish granular powder
Composition	Portland cement, selected sand, additives, pigments
Grain size	0 to 3 mm
VOC and formaldehyde content ISO/FDIS 11890-2/GC-MS	None (<10µg/l)
Resistance to fire as per BS EN 998 -1	Class A1

APPLICABLE STANDARDS

BS 5262: 1991
BS 5492: 1990
BS 4551: Part 2: 1998
ASTM C 150
ASTM C 926
ASTM C 897

INSTRUCTIONS FOR USE

SURFACE PREPARATION

The substrate must be clean, sound, and free from dust and all traces of oil or laitance.

The substrate must be dampened a few hours before the application of **weberpremix SRC-LW** and again 1 hour before application.

PRODUCT PREPARATION

Mix a 50 kg bag with 9 to 11 liters of clean cool water in order to obtain the consistency desired.
Mixing has to be done with an electric mixer.

PRODUCT APPLICATION

Apply the **weberpremix SRC-LW** using a tyrolean box or a power spray gun.



PACKAGING

Leb	Syria	Jordan	UAE	Qatar	Kuwait	KSA	Oman
50 kg	50 kg	50 kg	50 kg	50 kg	50 kg	50 kg	50 kg

CURING

Protect the newly applied plaster from sunshine and wind. The new plaster has to be cured with water for at least three days by spraying 3 to 4 times daily.

CONSUMPTION

Around 4 kg/m², depending on the substrate and the application method.

STORAGE

12 months after manufacturing date in original and non-open packaging, under cover, in dry condition, away from humidity, protected from extreme temperatures and direct sunlight.

SAFETY PRECAUTIONS

The product contains cement powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated area, and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting, in both cases seek medical attention. The product is non-flammable.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

NOTE

The information included on this Technical Data Sheet is the sole property of SODAMCO Holding. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

PG: 30

*Available only in GCC