

High-range water reducing/superplasticizing admixture

PRODUCT

Admix CF 100 is a superplasticizer based on synthetic polymers, that has a strong dispersing power over the fine particles of concrete and thus allows a higher mechanical resistance.

Admix CF 100 does not delay the setting of concrete and is capable for higher water reduction in concrete.

Admix CF 100 works on very low water/cement mixtures.

Admix CF 100 can be used on site to boost up the workability of the concrete mixture to any extent without danger of delay in setting.

PROPERTIES

- Increase concrete cohesion
- Increase compressive, tensile, and flexural strengths
- Produces high early strengths and can significantly increase mould utilization in precast works
- Can be used to gain economies due to possible cement reduction

SCOPE OF USE

Admix CF 100 is recommended for all cement types in the following areas:

- Heavily reinforced concrete works
- Paving and industrial floor
- Ready-mix concrete
- All concrete requiring fluid consistency
- Concrete with low W/C
- Precast concrete
- Cement based injection grout
- Works well with silica fume and slag
- Hollow core precast concrete elements
- Addition for workability at site
- Reduction in cement content

CHARACTERISTICS

Appearance	Liquid
Color	Brownish
Specific gravity at 20°C	1.210 ± 0.02 1.195± 0.015 (KSA)
Chloride content	Zero to BS 5075
Air entrainment	Less than 1% additional

STANDARDS

Admix CF 100 complies with:

ASTM C – 494 – Type F.

BS 5075 Part 1, BS EN 934, Part 2.

INSTRUCTIONS FOR USE

Admix CF 100 is totally miscible in water.

No extension to the batching time is necessary. Do not add to dry cement. **Admix CF 100** can be used on site to produce fluid concrete to a required workability. Make sure that the concrete is agitated for not less than 2 minutes at 15 - 20 rpm before casting.

For high early strength of concrete, use a lower w/c and a higher **Admix CF 100** dosage.

DOSAGE RATES

Trials should be conducted to determine the optimum dosage of **Admix CF 100** for a particular mix. A dosage of 800 to 2500 ml per 100 kg of cement is recommended. This may be changed to higher dosage in high ambient and mixture temperature conditions.

EFFECTS OF OVER DOSING

Admix CF 100 can be used at high dosages without retardation. Severe over dose of **Admix CF 100** will result in the following:

- Slight delay of the initial and final setting of the concrete mixture
- Slight increase in air entrainment
- Increased workability

No severe side effects are known with the history of use of **Admix CF 100**.

COMPATIBILITY

Admix CF 100 can be used in all types of portland and sulfate-resisting cements. For use with other cement types, contact Company's technical service department. **Admix CF 100** should be dispensed directly into the mixer and should not be pre-mixed with other admixtures. If other admixtures are to be used in concrete containing **Admix CF 100** they must be dispensed separately. Consult Company's Technical Dept. for advice.

SPECIFICATION CLAUSE

Admix CF 100, a superplasticizing concrete admixture manufactured to the following specification:

Admix CF 100 can be used in all concrete mixtures at dosage rate of 800 to 2500 ml per 100 kg of cement in accordance with the manufacture's instructions.

DISPENSING

It is preferable that liquid admixtures for concrete should be introduced into a mixer by means of automatic dispensing equipment. Such equipment can be supplied by our company.

PACKAGING

Admix CF 100 is supplied in:

Bulk, barrels

Storage tanks can be provided for bulk use.

STORAGE

Admix CF 100 can be stored up to 1 year from manufacturing date under cover, out of direct sunlight and protected from extreme temperatures.

HEALTH & SAFETY

In case of frost, the product recovers its properties after progressive thawing and homogenizing by agitation.

In case of contact with skin or eyes, rinse thoroughly with water. If irritation persists, seek medical attention.

If swallowed, do not induce vomiting and seek medical attention.

QUALITY STATEMENT

All our products are manufactured to comply with our internal QA/QC program and quality management system to ensure consistency and quality.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

NOTE

The information included on this Technical Data Sheet is the sole property of Saint-Gobain Middle East Holding SAL (previously SODAMCO Holding). The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.