

# Admix CF 334 M

ADMIXTURES & CONCRETE  
RELATED PRODUCTS

## HIGH-RANGE SUPERPLASTICIZING/ WATER REDUCING ADMIXTURE

### PRODUCT

Admix CF 334 M is formulated from synthetic polymers and is specially formulated to give exceptionally high water reduction and greater workability.

Admix CF 334 M is specially designed to perform significant dispersion to cement particles providing extremely workable characteristics with greatly reduced water demand.

### KEY BENEFITS

- High water reduction that allows high early and ultimate strengths
- High flow ability ensures easy placement
- Good cohesion, no segregation and minimal bleed water along with extremely high levels of workability
- Enhanced easier placement and delivery control
- High elastic modulus, low shrinkage and creep are achievable with graded coarse and fine aggregates
- Superior surface finishes
- Reduced Permeability
- Improved Cohesion
- Improved Rheology

### TYPICAL APPLICATIONS

- High performance concrete
- Highly workable concrete
- Concrete strength grade up to 35Mpa
- Ready-mixed concrete
- Mass concrete
- Pumped concrete
- Environmentally designed concrete structures
- Hot weather concreting

### SCOPE OF USE

ADMIX CF 334 M to ensure that plastic concrete remains workable for more than 90 minutes at high temperatures.

Ideal for construction of dams, locks, road works, architectural concrete, light or heavy prefabrication, ready-mix concrete, and pumped concrete.

### CHARACTERISTICS

Appearance	Liquid
Color	Brown
Specific gravity	1.45± 0.05
Chloride content	Zero to BS 5075

### APPLICABLE STANDARDS

Admix CF 334 M complies with:

EN 934-2 Table 2

ASTM C-494: Types F & G

BS 5075 Part 1 (superseded by EN 934-2)

### INSTRUCTION FOR USE

Admix CF 334 M is totally miscible in water. It is to be added to the concrete mixture during the mixing cycle at the same time as the mixing water. No extension to normal mixing time is necessary.

### DOSAGE

Trials should be conducted to determine the optimum dosage of Admix CF 334 M for a particular mixture. A dosage of 1000 to 3000 ml per 100 kg of cementitious materials can be practiced.

Dosage and batching

Dosage can be adjusted to meet mix design requirements or to meet specific job site conditions. Trial concrete mixes must be carried out to determine the appropriate dosage.

An Independent dispenser and feed line must be used. Admix CF 334 M can be added to the mixed concrete. Addition to any dry concrete mix is not recommended.

### EFFECTS OF OVER DOSING

A severe over dose of Admix CF 334 M will result in the following:

- Delay in setting
- Higher workability
- Higher Ultimate strength when curing practices are implemented as per ACI 308R

### COMPATIBILITY

Admix CF 334 M can be used in all types of Portland cements, sulfate-resisting cement, and concrete with cementitious materials. Admix CF 334 M should be dispensed directly into the mixer and should not be pre-mixed with other admixtures. If other admixtures are to be used in concrete containing Admix CF 334 M, they must be dispensed separately. Consult the company's technical dept. for advice.

# Admix CF 334 M

## SPECIFICATION CLAUSE

Admix CF 334 M is high-range Superplasticizing concrete admixture manufactured to the following specification:

Admix CF 334 M can be used in all concrete as mentioned at dosage between 1000 to 3000 ml per 100 kg of cementitious materials in accordance with the manufacturer's instructions.

Specific Gravity  $1.45 \pm 0.05$

Complying with:  
EN 934-2 Table 2  
ASTM C-494: Types F & G  
BS 5075 Part 1 (superseded by EN 934-2)

Composition: High molecular weight refined synthetic polymers derivatives and other refined chemicals.

## DISPENSING

It is preferable that liquid admixtures for concrete should be introduced into a mixer by means of automatic dispensing equipment. Such equipment can be supplied by the company.

## PACKAGING

Admix CF 334 M is supplied in: Bulk, barrels.  
Storage tanks can be provided for bulk use.

## STORAGE

Admix CF 334 M can be stored up to 1 year from manufacturing date under cover, out of direct sunlight and protected from extreme temperatures.

## HEALTH & SAFETY

In case of frost, the product recovers its properties after progressive thawing and homogenizing by agitation. In case of contact with skin or eyes, rinse thoroughly with water. If irritation persists, seek medical attention. If swallowed, do not induce vomiting and seek medical attention.

## QUALITY STATEMENT

All our products are manufactured to comply with our internal QA/QC program and quality management system to ensure consistency and quality.

## DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

## NOTE

The information included on this Technical Data Sheet is the sole property of SODAMCO Holding. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

Edition: 04/16-A

\*\*Available only in KSA

