

Admix CF 50 SL

ADMIXTURES & CONCRETE
RELATED PRODUCTS

HIGH-RANGE SUPERPLASTICIZER FOR FLUID CONCRETE

PRODUCT

Admix CF 50 SL is a chloride free, high-range, naphthalene-based superplasticizer, specially formulated for high early strength concrete mixture. Admix CF 50 SL has a powerful deflocculating and dispersing action with cement which facilitates the production of fluid, self-consolidating concrete without segregation from a no-slump concrete mixture.

PROPERTIES

Admix CF 50 SL produces:

- Concrete of similar workability with 20%-25% less water
- Increase concrete cohesion
- Increase compressive, tensile, and flexural strengths
- High early strength development, especially at low W/C ratios

SCOPE OF USE

Admix CF 50 SL is recommended for all cement types of ordinary portland cement and sulfate-resisting cement in the following areas:

- Heavily reinforced concrete works
- Paving and industrial floor
- Ready-mix concrete
- All concrete requiring a fluid consistency.
- Concrete with low W/C ratios.
- Precast concrete
- Works well with silica fume and GGBS
- Structures with close reinforcement where vibratory efforts are ineffective
- Can be used with white cement

CHARACTERISTICS

Appearance	Brown liquid.
Specific gravity at 20°C	1.190 ± 0.01
Chloride Content	Zero to BS 5075
Air entrainment	Less than 1.0% additional air is entrained

APPLICABLE STANDARDS

Admix CF 50 SL complies with:
ASTM C 494 Type F
BS 5075 Part 1, BS EN 934, Part 2.

INSTRUCTIONS FOR USE

Admix CF 50 SL is totally miscible in water.

No extension to the mixing time is necessary. Do not add to dry cement.

Admix CF 50 SL can be used at site to fluidify the concrete mixture to the required workability. Make sure that the mixture is agitated at not less than 1 rpm for 2 minutes to attain consistency before casting. For high early strength of concrete mixture, use with lower w/cm on higher Admix CF 50 SL dosage.

DOSAGE

Trials should be conducted to determine the optimum dosage of Admix CF 50 SL for a particular mixture. A dosage of 600 ml to 2100ml per 100 kg of cement is recommended.

The required dosage for a specific job with controlled delay in setting and workability should be determined by in situ trials.

EFFECTS OF OVER DOSING

A severe over dose of Admix CF 50 SL will result in the following:

- Delay of initial and final setting times.
- Slight increase in air entrainment
- Increase in workability
- Increase in early strength
- An increase in ultimate strength

COMPATIBILITY

Admix CF 50 SL can be used in all types of Portland and sulphate resisting cement. For use with other cement contact Company's technical service department. Admix CF 50 SL should be dispensed directly into the mixer and should not be pre-mixed with other admixtures. If other admixtures are to be used in concrete containing Admix CF 50 SL, they must be dispensed separately. Consult company's technical service Dept.

SPECIFICATION CLAUSE

Admix CF 50 SL, a plasticizing concrete admixture is manufactured to the following specification:

Admix CF 50 SL can be used in all concrete mixes as mentioned at a dosage between 600 ml to 2100 ml per 100 kg of cement in accordance with the manufacture's instructions.

Admix CF 50 SL

DISPENSING

It is preferable that liquid admixtures for concrete should be introduced into a mixer by means of automatic dispensing equipment. Such equipment can be supplied by our company.

PACKAGING

Admix CF 50 SL is supplied in:

Bulk, barrels.

Storage tanks can be provided for higher volume.

STORAGE

Admix CF 50 SL can be stored up to 1 year from manufacturing date under cover, out of direct sunlight and protected from extreme temperatures.

HEALTH & SAFETY

In case of frost, the product recovers its properties after progressive thawing and homogenizing by agitation. In case of contact with skin or eyes, rinse thoroughly with water. If irritation persists, seek medical attention. If swallowed, do not induce vomiting and seek medical attention.

QUALITY STATEMENT

All our products are manufactured to comply with our internal QA/QC program and quality management system to ensure consistency and quality.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

NOTE

The information included on this Technical Data Sheet is the sole property of SODAMCO Holding. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

Edition: 02/15-A



SODAMCO Holding Tayar Center Bloc B 1st flr. De Gaulle str. P.O.Box 55-44 Sin el Fil Beirut Lebanon
T +961 1 510863/4 M +961 3 380748 F +961 1 510862 sodamco@sodamco.com www.sodamco-weber.com

Lebanon . UAE . Syria . Qatar . KSA . Jordan . Kuwait . Oman