weber.ad sec P

formerly "Admix SEC P"

INTEGRAL WATERPROOFING ADMIXTURE IN POWDER FORM

PRODUCT

weber.ad sec P is a waterproofing admixture in powder form, designed for use in all cement-based applications, such as:

- plastering and rendering exposed to rain
- mounting mortar
- joint grout
- screed
- concrete

It minimises penetration of moisture into the mortar. It improves the workability of fresh mortar, plaster, or concrete.

Appearance	White powder
Specific gravity	0.8
Solubility	Partial in water
Capillarity	3.2 g/dm².min½
Cl- content	NIL
Admix SEC P is compatible with all portland cements.	

Capillarity at 28 days

	Capillarity
Control	6.75 g/dm².min½
Control + weber.ad sec P	3.2 g/dm².min½

INSTRUCTIONS FOR USE

weber.ad sec P is dosed for one bag of 50 kg cement:

- Spread the 1-kg bag over cement and aggregates.
 Usual mixture proportions shall be respected.
 Example for mortar: 1 part of cement for 3 parts of clean and selected sand. Do not pre- dissolve it in the mixing water
- Add the quantity of water required and mix well.
- Apply your mortar on a well-prepared substrate: clean, free from dust and all traces of oil or laitance.
 - Few hours before apply, dampen the support.
- Cure and protect the mortar as usual.

PACKAGING

weber.ad sec P is packed in 1 kg plastic bag

STORAGE

One year in dry condition of original packaging.

SAFETY PRECAUTIONS

The product contains very fine powder which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated area, and to wear protective gear for hands, eyes, and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning thoroughly with soap and water. In case of contact with eyes, wash thoroughly with clean water and seek medical attention. If swallowed, do not induce vomiting and seek medical attention. The product is non-flammable.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

NOTE

The information included on this Technical Data Sheet is the sole property of SODAMCO Holding. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

PG:37 Edition:07/14-A



