

Non shrink thixotropic repair mortar with fiber

PRODUCT

weberep 331 TX is a ready-to-use mortar mainly made of sand (reconstituted grain size range), special cement, fibres, and special additives that provide special properties: non-shrinking, thixotropic, high strength, high adhesion and compactness. The highly compacted grains slows down carbonation.

PROPERTIES

- Non-shrinking
- High strength
- Normal setting
- Good resistance to sea water and to high-sulphate water
- Thixotropic: It can be applied in a thick layer
- Prevents steel reinforcements from corrosion

SCOPE OF USE

- Repair of concrete surfaces, honeycombing, edges of steps and all types of load bearing situations.
- Restoring the structure of damaged construction: columns, slabs, vault, mats and dam overflows.
- Reinforcing of weakened structures such as balconies, pedestals and cornices.

CHARACTERISTICS

Active ingredients	hydraulic binders, synthetic fibres, without any chlorides or metal particles
Appearance	Grey Powder
Grain size	0 to 4 mm
Yield	Approx.12.5 liters / 25 kg bag
Thickness	5 to 50 mm in one coat
VOC and formaldehyde content ISO/FDIS 11890-2/GC-MS	None (<10µg/l)

*Compressive Strength BS EN 12190 at at 22°C ± 1: 7 days 28 days	>50 MPa >60 MPa
*Flexural Strength - BS EN 196-1 at 22°C ± 1 28 days	>8 MPa
*Tensile Strength: 7 days (BS EN 6319 Part 7) 28 days (BS EN 6319 Part 7)	3.5 MPa 4 MPa
*Adhesion Strength: 28 days (BS EN 1881 Part 207)	> 1.5 MPa



PACKAGING

Leb	Syria	Jordan	UAE	Qatar	Kuwait	KSA	Oman
-	-	-	-	-	25 kg	-	-

*Test for compatibility with potable water

BS 6920 Part 2.6: 2000

Complies

**Results obtained at 15% water under lab. condition at 22°C ± 1.*

**Properties listed above are only based on controlled laboratory samples and tests: Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.*

APPLICABLE STANDARDS

BS EN 196-1: 1994
BS EN 6319 Part 2
BS EN 6319 Part 3
BS EN 6319 Part 7
BS 6920 Part 2.6: 2000
BS EN 12190
BS 1881 Part 207: 1992 section B

INSTRUCTIONS FOR USE

SUBSTRATE PREPARATION

weberep 331 TX may be applied on sound concrete, masonry, rock or similar materials.

Remove damaged concrete and laitance by chipping with a pick or cold-chiselling to get a rough surface.

The area must be surrounded by clean edges. Do not feather edges.

The surface must also be free from any trace of grease or oil.

Brush or scrape corroded steel with a metal brush, or sand it to remove all rust particles.

Remove dust from all surfaces to be fixed.

For an optimal protection of steel, apply **weberep 370 PF** by brush prior to **weberep 331 TX**.

Saturate the surface with water by copiously spraying just before application, and if possible, 6 hours before application as well.

PRODUCT PREPARATION

Mix a 25 kg bag **weberep 331 TX** with 3.75 to 4 litres of clean water until a smooth paste is obtained.

PRODUCT APPLICATION

weberep 331 TX can be applied:

- Manually with a trowel.
- By using a dry or wet spraying machine.
- By pumping.

weberep 331 TX must be used within one hour from mixing depending on temperature & site condition.

For thickness more than 50 mm, it is recommended to apply **weberep 331 TX** in 2 layers. When the first coat is applied it must be directly roughened to increase bonding with the second coat.

Re-mixing with an extra amount of water is forbidden.

After application, cure the exposed surface by spraying cool water for 3 days, by using a curing compound like **weberad cure WH** or **weberad cure Y 40** or by covering with properly secured plastic sheeting. Ideal application temperature is between + 5°C and + 35°C. If the application temperature is higher than 35°C, make sure to use cool water to keep the mixed mortar temperature below 30°C.

STORAGE

12 months after manufacturing date in original and non-open packaging, under cover, in dry condition, away from humidity, protected from extreme temperatures and direct sunlight.

SAFETY PRECAUTIONS

The product contains cement powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated area, and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning thoroughly with soap and water. In case of contact with eyes, wash thoroughly with clean water and seek medical attention. If swallowed, do not induce vomiting and seek medical attention. The product is non-flammable.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

NOTE

The information included on this Technical Data Sheet is the sole property of SODAMCO Holding. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

*Available only in Kuwait