

# Admix CF 100 P

ADMIXTURES & CONCRETE  
RELATED PRODUCTS

## HIGH-RANGE / WATER REDUCING / SUPERPLASTICIZING ADMIXTURE FOR PRECAST CONCRETE

### PRODUCT

Admix CF 100 P is a superplasticizer based on synthetic polymers, that has a strong dispersing power over the fine particles of concrete, hence allowing higher mechanical properties and high early compressive strength.

Admix CF 100 P does not delay the setting time of the concrete and is capable to achieve higher water reduction in concrete. Admix CF 100 P works even in concrete with very low water/cementitious materials ratio containing supplementary cementitious materials, such as GGBS and silica fume.

Admix CF 100 P can be used on site (re-tempering) to boost up the workability of the concrete mixture to any extend fluidity without danger of delay in setting.

### PROPERTIES

- Increase concrete cohesion
- Increase compressive, tensile, and flexural strengths
- Produces high early strengths and can significantly increase mould utilization in precast works
- Can be used to gain economies due to a possible cement reduction

### SCOPE OF USE

Admix CF 100 P is recommended for all cement types in the following areas:

- Heavily reinforced concrete works
- Paving and industrial floors
- Ready-mix concrete
- Concrete with low W/CM
- Precast concrete
- Hollow core precast concrete elements
- Improvement of concrete workability on site
- Reduction in cement content

### CHARACTERISTICS

Appearance	Liquid
Color	Brownish
Specific gravity at 20°C	1.21 ± 0.03
Chloride content	Zero to BS 5075
Air entrainment	Less than 1% additional air is entrained.

### APPLICABLE STANDARDS

Admix CF 100 P complies with:

ASTM C – 494 – Type F.

BS 5075 Part 1, BS EN 934, Part 2.

### INSTRUCTION FOR USE

Admix CF 100 P is totally miscible in water. No extension to the batching time is necessary. Do not add to dry cement. Admix CF 100 P can be used on site to produce fluid concrete to a required workability. Make sure that the concrete is agitated for not less than 2 minutes at 15- 20 rpm before casting.

For high early strength of concrete, use a lower W/C and higher Admix CF 100 P dosage.

### DOSAGE

Trials should be conducted to determine the optimum dosage of Admix CF 100 P for a particular mixture. A dosage of 800 to 2250 ml per 100 kg of cementitious materials is recommended. This may be changed to higher dosage in high ambient and mixture temperature conditions.

### EFFECTS OF OVER DOSING

Admix CF 100 P can be used at high dosage rates without any retardation. A severe over dosage of Admix CF 100 P will result in the following:

- Very slight delay of the initial and final setting times of the concrete mixture.
- Very Slight increase in air entrainment.
- Increase in workability.

No more severe side effects are known with the history of Admix CF 100 P.

### COMPATIBILITY

Admix CF 100 P can be used in all types of portland and sulfate-resisting cements, including those containing supplementary cementitious materials. For use with other cements, contact the company's technical service department. Admix CF 100 P should be dispensed directly into the mixer and should not be pre-mixed with other admixtures. If other admixtures are to be used in concrete containing Admix CF 100 P they must be dispensed separately. Consult the company's technical dept. for advice.

# Admix CF 100 P

## SPECIFICATION CLAUSE

Admix CF 100 P, a superplasticizing concrete admixture manufactured to the following specification:

Admix CF 100 P can be used in all concrete mixtures as mentioned, at dosage rate between 800 and 2250 ml per 100 kg of cementitious materials in accordance with the manufacture's instructions.

## DISPENSING

It is preferable that liquid admixtures for concrete should be introduced into a mixer by means of automatic dispensing equipment. Such equipment can be supplied by the company

## PACKAGING

Admix CF 100 P is supplied in:

Bulk, barrels

Storage tanks can be provided for bulk use.

## STORAGE

Admix CF 100 P can be stored up to 1 year from manufacturing date under cover, out of direct sunlight and protected from extreme temperatures.

## HEALTH & SAFETY

In case of frost, the product recovers its properties after progressive thawing and homogenizing by agitation. In case of contact with skin or eyes, rinse thoroughly with water. If irritation persists, seek medical attention. If swallowed, do not induce vomiting and seek medical attention.

## QUALITY STATEMENT

All our products are manufactured to comply with our internal QA/QC program and quality management system to ensure consistency and quality.

## DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

## NOTE

The information included on this Technical Data Sheet is the sole property of SODAMCO Holding. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

Edition: 04/16-A

\*Available only in Gulf & KSA

