

# Admix CF 88 RN

ADMIXTURES & CONCRETE  
RELATED PRODUCTS

## HIGH-RANGE WATER REDUCING/ RETARDING / SUPERPLASTICIZING ADMIXTURE

### PRODUCT

Admix CF 88 RN is designed as a multi-purpose superplasticizer. It can be used for moderate to low w/c concrete.

This special formulation enables Admix CF 88 RN to retain concrete workability for a longer time. It can maintain good mix appearance without segregation or bleeding. At intentionally higher dosages, Admix CF 88 RN has the effect of a setting retarder.

### PROPERTIES

- High workability produced is recommended for congested reinforced structures
- Extended setting times allow effective hot weather concreting
- Allows quicker consolidation
- Improves surface appearance
- No segregation at higher dosages
- Improves pumpability
- Can be used to gain economy due to possible cement reduction

### SCOPE OF USE

Admix CF 88 RN is used to ensure that plastic concrete remains workable for more than 1 hour at high temperature. Ideal for construction of dams, locks, road works, architectonic concrete, light or heavy prefabrication, ready-mix concrete, and pumped concrete.

### CHARACTERISTICS

|                          |  |
|--------------------------|--|
| Appearance               | Liquid   |
| Color                    | Brown  |
| Specific gravity at 20°C | 1.045± 0.01  |
| Chloride content         | Zero to BS 5057  |
| Air entrainment          | Up to 1% depending on the dosage and mixture proportioning |

### APPLICABLE STANDARDS

Admix CF 88 RN complies with:  
ASTM C 494 Type D  
BS 5075 Part 1, BS EN 934, Part 2.

### INSTRUCTIONS FOR USE

Admix CF 88 RN is totally miscible in water. It is to be added to the concrete during the mixing cycle at the

same time as the mixing water. No extension to normal mixing time is necessary.

### DOSAGE

Trials should be conducted to determine the optimum dosage of Admix CF 88 RN for a particular mixture. A dosage of 300 to 1300 ml per 100 kg of cement is recommended.

The required dosage for a specific job with controlled delay in setting and workability should be determined by in situ trials.

### EFFECTS OF OVER DOSING

A severe over dose of Admix CF 88 RN will result in the following:

- Delay in setting
- Slight increase in air content
- Higher workability
- Higher ultimate strength

In case of over dosage, precautions should be taken not to disturb the surface area. With proper curing, the ultimate strength of the structure should not be adversely affected.

### COMPATIBILITY

Admix CF 88 RN can be used in all types of portland cement and sulfate resisting cement. For use with other cements contact the company's technical service department. Admix CF 88 RN should be dispensed directly into the mixer and should not be pre-mixed with other admixtures. If other admixtures are to be used in concrete containing Admix CF 88 RN, they must be dispensed separately. Consult the company Technical Dept. for advice.

### SPECIFICATION CLAUSE

Admix CF 88 RN, a retarding, plasticizing concrete admixture is manufactured to the following specification:

Admix CF 88 RN can be used in all concrete as mentioned at dosage between 300 ml to 1300ml per 100kg of cement in accordance with the manufacture's instructions.

# Admix CF 88 RN

Specific Gravity at 20°C:  $1.125 \pm 0.015$

Complying to ASTM C 494 Type D

Composition: High molecular weight refined naphthalene derivatives and other refined chemicals.

## DISPENSING

It is preferable that liquid admixtures for concrete should be introduced into a mixer by means of automatic dispensing equipment. Such equipment can be supplied by the company.

## PACKAGING

Admix CF 88 RN is supplied in:

Bulk, barrels.

Storage tanks can be provided for bulk use.

## STORAGE

Admix CF 88 RN can be stored up to 1 year from manufacturing date under cover, out of direct sunlight and protected from extreme temperatures.

## HEALTH & SAFETY

In case of frost, the product recovers its properties after progressive thawing and homogenizing by agitation. In case of contact with skin or eyes, rinse thoroughly with water. If irritation persists, seek medical attention. If swallowed, do not induce vomiting and seek medical attention.

## QUALITY STATEMENT

All our products are manufactured to comply with our internal QA/QC program and quality management system to ensure consistency and quality.

## DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

## NOTE

The information included on this Technical Data Sheet is the sole property of SODAMCO Holding. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

Edition: 02/15-A

