

# Admix CF JM2

ADMIXTURES & CONCRETE  
RELATED PRODUCTS

## SUPERPLASTICIZER - HIGH SLUMP RETENTION

### PRODUCT

Admix CF JM2 is composed of modified naphthalene and retarding additives.

Admix CF JM2 is a concrete superplasticizer that enables the increase in concrete fluidity over extended period of time without mitigating homogeneity and resistance to segregation.

### PROPERTIES

Admix CF JM2 acts simultaneously on the following:

- Dispersing of fine particles
- Cohesion of fresh concrete
- Setting of concrete

When using dosage lower than those necessary for fluidification Admix CF JM2 allows the preparation of plastic concrete, with an attractive appearance and an elevated mechanical resistance, and therefore an optimization of the dosage in cement per m<sup>3</sup>.

### SCOPE OF USE

Admix CF JM2 is recommended for all cement types, in the following areas:

- Ready to use concrete
- Heavily reinforced concrete works
- Incubated concrete
- Paving and industrial floors
- Pumped concrete
- Fluid concrete for long maintenance of slump

Admix CF JM2 is recommended when using silica fume.

### CHARACTERISTICS

Appearance	Brown liquid
Specific gravity	1.09 ± 0.02

### APPLICABLE STANDARD

Applicable standard: ASTM C 494 Type G.

### INSTRUCTIONS FOR USE

Admix CF JM2 is totally miscible in water.

Admix CF JM2 is introduced into the mixer at the same time as the mixing water, when a constant plasticity is required.

### DOSAGE RATES

From 0.3 to 1.5 kg / 100 kg of cement.

### SPECIAL ADVICE

#### COMPOSITION CONCRETE

The composition of the concrete before being plasticized must be established with care. The grain size of aggregates must include a proportion of fine elements, comparable to those of pumped concrete.

#### MAINTENANCE OF FLUIDITY

The delay during which the plasticized concrete remains fluid is variable according to the temperature, to the original consistency of concrete, to the nature and to the dosage of cement, etc.

Admix CF JM2 allows prolonged fluidity retention, which is proportionally to the dosage of the admixture.

Previous in-situ trials will allow the determination of the optimal dosage of Admix CF JM2.

### PACKAGING

Admix CF JM2 is supplied in:

Bulk

200 and 25 lit. drums

### STORAGE

Admix CF JM2 can be stored up to 1 year from manufacturing date under cover, out of direct sunlight and protected from extreme temperatures.

### HEALTH & SAFETY

In case of frost, the product recovers its properties after progressive thawing and homogenizing by agitation. In case of contact with skin or eyes, rinse thoroughly with water. If irritation persists, seek medical attention. If swallowed, do not induce vomiting and seek medical attention.

### QUALITY STATEMENT

All our products are manufactured to comply with our internal QA/QC program and quality management system to ensure consistency and quality.

### DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without

# Admix CF JM2

prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

## NOTE

The information included on this Technical Data Sheet is the sole property of SODAMCO Holding. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

Edition: 08/15-A

\*\*Available only in MENA



SODAMCO Holding Tayar Center Bloc B 1st flr. De Gaulle str. P.O.Box 55-44 Sin el Fil Beirut Lebanon  
T +961 1 510863/4 M +961 3 380748 F +961 1 510862 [sodamco@sodamco.com](mailto:sodamco@sodamco.com) [www.sodamco-weber.com](http://www.sodamco-weber.com)

Lebanon . UAE . Syria . Qatar . KSA . Jordan . Kuwait . Oman