

# weber.ad 200 PVA (Jordan)

ADMIXTURES & CONCRETE  
RELATED PRODUCTS

## PVA-BASED BONDING AGENT FOR MORTAR AND CONCRETE

### PRODUCT

weber.ad 200 PVA is a synthetic resin emulsion, non-corrosive and non toxic, used as a bonding agent for mortar, rendering and concrete on all surfaces, even in damp atmosphere. weber.ad 200 PVA may be used as a primer or an admixture for mortar, plaster and concrete. It increases waterproofing and curing effects, and improves plasticity.

### SCOPE OF USE

- Bonding of thin coating on smooth concrete without scabbing
- Bonding of thin topping on floor slab without scabbing
- Bonding between 2 phases of concreting
- Repair of joint spalling
- Admixture to spatter-dash key slurry
- Repairs of toppings
- Bonding additive for mortar and grouting tiles

### CHARACTERISTICS

Appearance	White liquid
Density at 20°C	1.1
Viscosity Brookfield	50 000 Cps at 25°C
pH	7.5 to 8.5

### INSTRUCTIONS FOR USE

Substrates must be clean, sound and free from dust, laitance and greasy matter. Stir thoroughly before use.

weber.ad 200 PVA must be dissolved in the mixing water. Never work below + 5°C and beyond + 45°C.

#### Bonding new concrete to old concrete

Mix 1 part of weber.ad 200 PVA with 1 part of water. Apply with a brush or a spray, then bond the new concrete while the solution is still tacky.

#### Key coat

Add to the key coat around 6 kg of weber.ad 200 PVA per 50 kg cement. Apply the slurry uniformly and cure it for 3 days.

#### Plaster, mortar and grout

Make a conventional dry mix using screened and clean sand.

Add weber.ad 210 PV to the mix at the ratio of 7% to 15% of cement weight.

### PACKAGING

weber.ad 200 PVA is supplied in 20 kg, 200 kg drum.

### STORAGE

6 months in dry conditions and original packaging. To be stored protected against frost. In case of frost, weber.ad 200 PVA recovers its properties after progressive thawing.

### SAFETY PRECAUTIONS

Avoid prolonged contact with skin. Wear protective gear for hands & eyes. Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting, in both cases seek medical attention. The product is non-flammable.

### DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

### NOTE

The information included on this Technical Data Sheet is the sole property of SODAMCO Holding. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

PG:37

Edition: 03/16-A

\*Available only in Jordan

