

Gypsum based ready mixed finishing coat

PRODUCT

weberpremix SGP-2 is a ready mixed render based on hemi-hydrated gypsum. It's used for finishing interior cement or gypsum based plaster prior painting.

SCOPE OF USE

- Gypsum based plaster
- Cement based plaster

CHARACTERISTICS

Appearance	Off-white powder
Size of grains	0 to 0.5 mm
Setting time	Around 2 hours 30 minutes
Dried density	1.2
Composition	Gypsum, selected fillers, additives

Acoustic & Fire rating properties:

	without plaster	with plaster assemblies (16mmSGP1 & 3mm SGP2)
STC av.value (ASTM E 90-02 section 9.0)	55	58
Transmission of heat properties (ASTM E-119)	177 min.	235 min.

APPLICABLE STANDARDS

ASTM C 28.

BS EN 13279-1.

ASTM E 90-02 section 9.0 for sound transmission loss/acoustic performance

ASTM E- 119 for fire resistance test.

INSTRUCTIONS FOR USE

SURFACE PREPARATION

Substrates must be sound, clean, dust free and free from all traces of oil and laitance. Few hours before apply, dampen the support.

PRODUCT PREPARATION

Mix a 40 kg bag with 20 liters (17.5 L. for 35 kg bag) of water in order to obtain a homogeneous paste.

PRODUCT APPLICATION

weberpremix SGP-2 may be applied manually with a steel trowel. Once applied on the surface, the product must be leveled and smoothed before drying. As **weberpremix SGP-2** is a finishing coat, thickness of application should not exceed 3 mm.



PACKAGING

Leb	Syria	Jordan	UAE	Qatar	Kuwait	KSA	Oman
40 kg	40 kg	40 kg	40 kg	35 kg	40 kg	35 kg	40 kg

Ideal application temperature is between + 5°C and + 35°C.

CONSUMPTION

1.3 kg per m² and 1mm thickness.

STORAGE

12 months after manufacturing date in original and non-open packaging, under cover, in dry condition, away from humidity, protected from extreme temperatures and direct sunlight.

SAFETY PRECAUTIONS

It is preferable that the application be done in a ventilated area, and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting, in both cases seek medical attention. The product is non-flammable.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use,

and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

NOTE

The information included on this Technical Data Sheet is the sole property of SODAMCO Holding. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

PG: 30