

## One coat fiber reinforced cement plaster

### PRODUCT

**weberpremix SSP-200** is a fiber reinforced, portland cement based plaster containing silica fume, fibers and other admixtures that give a high strength and shrinkage controlled plaster. It is specially designed for use in one coat stucco applications to be sprayed onto dried and cured shotcrete used in Insulated Sandwich Panel System (ISPS).

For low strength requirement, our **weberpremix SP-1** can be used as alternative to **weberpremix SSP-200**.

### PROPERTIES

- High strength
- Low rebound
- Normal setting
- Allows for thicker single pass applications
- Prevents steel reinforcements from corrosion
- Reduced permeability

### SCOPE OF USE

**weberpremix SSP-200** can be used in residential and light commercial areas to any surface suitable for accepting fresh plaster. Shotcrete, cement based substrate, old concrete are common substrate.

### CHARACTERISTICS

Active ingredients	hydraulic binders, synthetic fibers, without any chlorides or metal particles
Appearance	Grey Powder
Powder density	1.28
Grain size	0 to 2.5 mm
Mixing water	9 to 10 liters / 50 kg bag 4.5 to 5 liters / 25 kg bag
Yield	30 liters / 50 kg bag 15 liters / 25 kg bag
Thickness	5 to 30 mm in one coat
Fresh density ASTM C 185- 02 section 5.2	Around 2.000
Resistance to fire as per BS EN 998-1	Class A1

Tests performed under laboratory conditions.

*Compressive Strength - ASTM C109 M at 22°C± 1:	1 day	7 MPa
	7 days	21 MPa
	28 days	25 MPa



### PACKAGING

Leb	Syria	Jordan	UAE	Qatar	Kuwait	KSA	Oman
25 kg	25 kg	25 kg	25 kg	25 kg	25 kg	25 kg	25 kg
50 kg	50 kg	50 kg	50 kg	50 kg	50 kg	50 kg	50 kg

*Flexural Strength - BS EN 196-1 at 22°C± 1:	1 day 7 days 28 days	1.5 MPa 2.5 MPa 5 MPa
*Adhesion Strength: 28 days (BS 1881 Part 207)		> 0.5 MPa

\* Results obtained at 19% water under lab condition at 22°C± 1.

### INSTRUCTIONS FOR USE

#### SUBSTRATE PREPARATION

the shotcrete should be installed, dried and cured.

#### PRODUCT PREPARATION

Each bag of 50 kg **weberpremix SSP-200** requires around 9.5 liters of clean water. A 25 kg will need approx. 4.75 liters of clean water.

#### PRODUCT APPLICATION

**weberpremix SSP-200** should be applied using the wet-mix process. **weberpremix SSP-200** is pre-mixed before being loaded into a hopper, from which it is pumped through the delivery hose and spray-applied with compressed air added at the nozzle via a separate hose.

**weberpremix SSP-200** must be used within one hour from mixing.

Usually 15 mm thickness is required to fill any cracks, grooves or other imperfections in the shotcrete to ensure complete coverage. For thickness more than 30 mm, it is recommended to apply **weberpremix SSP-200** in 2 layers. When the first coat is applied it must be directly roughened to increase bonding with the second coat.

The finishing of the top layer will depend on the decorative finishing that will be associated to the system. **weberpremix SSP-200** can be smoothed with a steel trowel or kept rough using wooden or plastic trowel.

Re-mixing with an extra amount of water is forbidden.  
Protect the surface with properly secured plastic sheeting.  
Ideal application temperature is between +5 °C and +35 °C.

## STORAGE

12 months after manufacturing date in original and non-open packaging, under cover, in dry condition, away from humidity, protected from extreme temperatures and direct sunlight.

## SAFETY PRECAUTIONS

The product contains cement powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated area, and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting, in both cases seek medical attention. The product is non-flammable.

## DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

## NOTE

The information included on this Technical Data Sheet is the sole property of SODAMCO Holding. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

PG: 30