

SAINT-GOBAIN



# weberpremix fine finish

Water resistant premixed putty for cement based substrate

> Plastering Mortars

Leb	Jordan	Egypt	UAE	Qatar	Kuwait	KSA	Oman
-	-	-	-	20kg	-	25kg	-
40kg	-	40kg	50kg	-	50kg	50kg	50kg

#### **PRODUCT**

weberpremix fine finish is a pre mixed white powder. It is used to achieve proper smoothening of concrete surface and to eliminate irregularities of concrete, bubbles or cracks. As weberpremix fine finish is a water-resistant cement-based putty it can be applied externally and internally on walls and ceiling such as bathrooms and kitchens. It has better compatibility with the base plaster and forms a durable base for paints. premix fine finish can be applied directly on fairfaced concrete.

# **ADMISSIBLE SUBSTRATES**

Any kind of cement based substrate.

#### **ASSOCIATED FINISHES**

- Plastic decorative coating
- Wall paper

CHARACTERISTICS				
Appearance	White powder			
Bulk density	1.17			

Composition	Synthetic resins, mineral charges and additives			
Wet mix life	Around 1 hour at 20°C			
Density	1.45 ± 0.05			
Consumption	1-1.1 kg/m²/1mm thickness depending on the substrate			

# **APPLICABLE STANDARDS**

ASTM C348, ASTM C349, ASTM C136, ASTM C807

### **INSTRUCTIONS FOR USE** SUBSTRATE PREPARATION

Substrates must be clean, sound, dust free and free from all traces of oil and laitance. Traces of mould joints must be levelled.

# PRODUCT PREPARATION

The weberpremix fine finish paste is obtained by mixing a 50 kg bag with 24 to 25 lit. (40 kg bag in MENA countries with 19.2 to 20 lit. and 25 kg bag in KSA with 11.25 to 12 lit.) of clean cool water, using a suitable mixer. The paste should be mixed vigorously until it is fully homogeneous.

#### PRODUCT APPLICATION

Product is applied using a stainless steel trowel or stucco blade. Surfacing is obtained with one or several passes depending on requested finish. Two coats can be applied, each 1 mm max.



# Plastering Mortars

thickness of more than 3 mm is not recommended. To make sure that the first coat is set and dried before applying the second one. No water curing is needed between layers. In hot weather, it is recommended to moisten the substrate prior the application. Clean tools with water immediately after use. Ideal application temperature is between + 5°C and + 35°C.

#### **STORAGE**

12 months after manufacturing date in original and non-open packaging, under cover, in dry condition, away from humidity, protected from extreme temperatures and direct sunlight.

#### **SAFETY PRECAUTIONS**

The product contains cement powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated area, and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting, in both cases seek medical attention. The product is non-flammable.

#### **DISCLAIMER**

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

#### NOTE

The information included on this Technical Data Sheet is the sole property of Saint-Gobain Middle East Holding SAL (previously SODAMCO Holding. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

