

## General purpose mortar, with accelerated early setting

### PRODUCT

**weberep supermix** is a dry ready mixed mortar that requires addition of water only. It is made of hydraulic binders, calibrated aggregates and resins. Its formulation provides specific properties: accelerated setting, compensated shrinkage, good mechanical strengths.

### SCOPE OF USE

This product is particularly adapted for all common repairs and cavities filling in hollow blocks and concrete. weberep supermix is aimed at electricians, plumbers, masons or all private persons

### CHARACTERISTICS

Aspect	Grey Powder
Grain size	0 to 2.5mm
Powder density	1.35
Compressive strength	>10 MPa (28days)

### INSTRUCTIONS FOR USE

**weberep supermix** is to be mixed with clean water.

Dosage of water is around 4 lit./25kg.

Mixing is done manually.

The product is applied manually using a trowel. The support must be sound, clean, free from greasy matters or dust. Moisten the surface before application.

The setting begins around 45 min after mixing (at 20°C).

Ideal application temperature is between + 5°C and + 35°C.

If the application temperature is higher than 35 °C, make sure to use cool water to keep the mixed mortar temperature below 30 °C.

### CURING

Protect the newly applied material from sunshine and wind.

The new material has to be cured with water for at least three days by spraying 3 to 4 times daily.

### YIELD

25 kg bag gives 15 liters of mortar.

### STORAGE

12 months after manufacturing date in original and non-open packaging, under cover, in dry condition, away from humidity, protected from extreme temperatures and direct sunlight.

### SAFETY PRECAUTIONS

The product contains cement powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated



### PACKAGING

Leb	Syria	Jordan	UAE	Qatar	Kuwait	KSA	Oman
25 kg	25 kg	25 kg	25 kg	25 kg	25 kg	25 kg	25 kg

area, and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning thoroughly with soap and water. In case of contact with eyes, wash thoroughly with clean water and seek medical attention. If swallowed, do not induce vomiting and seek medical attention. The product is non-flammable.

### DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

### NOTE

The information included on this Technical Data Sheet is the sole property of SODAMCO Holding. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

PG:23

\*\*Available only in MENA

