# weber jointseal PU (Qatar)

### One component polyurethane sealant

#### **PRODUCT**

weber jointseal PU is reliable low modulus polyurethane based elastomeric sealant, allowing a high degree of elongation. It cures under the effect of atmospheric humidity to form a flexible and resistant joint with very good adhesion on most materials. After stretching, it recovers its performances and its resistance to climatic ageing, ultra violet rays and atmospheric corrosion. It can be later painted after full curing: a preliminary test is recommended.

The **weber jointseal PU** sealant conforms to the requirements of ASTM C 920, "Standard Specification for Elastomeric Joint Sealants", Type S, Grade NS, Class 25, Use NT, Tl, A and M. **weber jointseal PU** doesn't stain the marble or granite stone.

#### **SCOPE OF USE**

weber jointseal PU is used:

- · For waterproofing of masonry joints.
- · In expansion joints in concrete structures.
- As joint sealant between heavy and light prefabricated concrete elements.
- As a joint sealant in metal structures, in cladding, in door and window frames (metal, wood, aluminum, PVC).
- · As a sealant for cracks.
- · As a sealant in glass blocks.
- · For bonding baked clay and concrete roof tiles.
- · In the joint between the precast panels.

**weber jointseal PU** has a good adhesion without primer on current materials: concrete, mortar, wood, most lacquered metals, polyester, glass, Rigid PVC, stone, ceramic tiles...

CHARACTERISTICS	
Appearance	Pasty Polyurethane
	elastomer
Colors available	White, grey, beige,
(available upon request)	brown, black
Density	1.32 ± 0.03 Kg/L
Elongation ISO 37:2011	> 600%
Shore A hardness ISO 868:2003	25
Movement accomodation	25%
factor - ISO 9047:2001	
Peel strength (Glass)	>35 N
ASTM C 794-01	
Peel strength (Aluminum)	>40 N
ASTM C 794-01	
Peel strength (Concrete)	>40 N
ASTM C 794-01	
Staining and color change (Mortar)	None
ASTM C 1248-18	



#### **APPLICABLE STANDARDS**

Meets class 25 LM construction sealant (type F) according to ISO 11600 standard.

ASTM C 920

### INSTRUCTIONS FOR USE SURFACE PREPARATION

All surfaces should be clean, dry, free from grease, oil or dust and any contaminants that could harm bonding. Remove old sealant residue completely before applying new sealant. we recommend cleaning concrete with a metal brush.

Check the compatibility of the solvent used with the substrates.

When using solvents, extinguish all sources of ignition and carefully follow the safety and handling instructions given by us.

If necessary, rub down metal surfaces beforehand.

After rubbing down, the surface should be re-cleaned.

Allow the substrate to dry after degreasing.

For a cleaner job, protect the edges of the joint with self adhesive masking tape.

If required place a backer rod inside the gap to be filled for correcting the depth.

#### **PRODUCT APPLICATION**

weber jointseal PU can be applied by a manual or pneumatic



# weber jointseal PU (Qatar)

gun.

After application, use a putty knife to smooth the joint (before skin formation) with soapy water.

This product should be used within 24 hours of opening the sausage; otherwise, the sealant could harden inside.

Do not apply at a temperature under +5°C. In cold weather, store the packaging at about +20°C before use.

Avoid any contact with non-cured MS, hybrid PU or silicone sealants as well as with alcohols or ammonia during curing. In case of problem, contact company for advice.

#### **STORAGE**

12 months from manufacturing date, stored in a dry and cool rooms in their sealed and original sausages. Protect the material against moisture and direct sunlight. Storage temperature:  $+5^{\circ}\text{C}$  /  $+25^{\circ}\text{C}$ .

#### **SAFETY PRECAUTIONS**

Application should be done in a ventilated area away from any heat source. Wear protective gear for hands and eyes and avoid breathing of vapor. If mixed resin comes into contact with the skin, it should be promptly removed before hardening, followed by thoroughly washing the skin with soap and water. In case of heavy vapor inhalation, place affected person in an open-air area. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting. In all cases, seek medical attention. In case of fire, use CO2 foam to extinguish. Tightly seal containers when not in use, store them away from heat and carefully dispose empty ones.

#### **DISCLAIMER**

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

#### NOTE

The information included on this Technical Data Sheet is the sole property of SODAMCO Holding. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

