

## SBR Latex-based bonding agent

### PRODUCT

**weberad 240 LTX** is a styrene-butadiene copolymer latex (SBR) used as a waterproof and bonding agent added to concrete and mortar.

### PROPERTIES

**weberad 240 LTX** is added to cement based mortars and concrete to provide following properties:

- Good flexural / compressive strength
- Resistance to abrasion
- Resistance to fuel, oils and salt
- Limited shrinkage
- Increased waterproofing and durability
- Improved adhesion

### SCOPE OF USE

- Industrial flooring
- Concrete repair
- Bonding slurries
- Watertight compartments
- Potable water reservoirs
- Cement based adhesives
- External and internal mortars
- Bonding of fresh concrete to hardened concrete

### CHARACTERISTICS

Appearance	White liquid
Density at 20°C	Approx. 1
pH	8 ± 1
VOC (USEPA Method 24)	0.1 g/l (less water)

### INSTRUCTIONS FOR USE

#### Spatterdash keying mix

The surface must be sound, clean and free from oil and grease.

In order to provide a good bonding slurry, **weberad 240 LTX** is added with the mixing water at the ratio of 4% of cement weight.

The slurry should be projected manually or sprayed mechanically. Cure with water for 3 days.

#### Floor screed

The surface must be thoroughly cleaned and free from oil and grease.

Prime the substrate with a slurry made with cement, sand and **weberad 240 LTX** diluted in water (**weberad 240 LTX** / water ratio in volume: 1/1).

While the surface is still tacky, pour the concrete. The screed

performances may also be improved by adding **weberad 240 LTX** from 2 to 6 % of the cement weight.

Spread the mix on the substrate and adjust it at the required level.

#### Better performances mortar

Quality of cement based traditional mortars may also be improved by adding **weberad 240 LTX** during the mix. Recommended dosage: from 2 to 6% of the cement weight, to be added to the mixing water.

### PACKAGING

**weberad 240 LTX** is supplied in:

MENA: 1kg, 5 kg, 25 kg and 200 kg drums.

GCC & KSA: 5 lit, 20 lit, 160 lit, 200 lit drums and 1000 lit. containers.

### STORAGE

**weberad 240 LTX** has a high storage stability from - 20°C to + 45°C. Stir always before use.

Can be stored up to 6 months after manufacturing date, in original packaging.

### SAFETY PRECAUTIONS

Avoid prolonged contact with skin. Wear protective gear for hands & eyes. Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting, in both cases seek medical attention. The product is non-flammable.

### DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

### NOTE

The information included on this Technical Data Sheet is the sole property of SODAMCO Holding. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.