

Multipurpose neutral silicone sealant

PRODUCT

weber silicone N is a neutral, one component multipurpose use silicone, which cures under the influence of humidity from the air to form a durable elastic rubber. **weber silicone N** is intended for sealing and grouting joints and to protect against moisture.

SCOPE OF USE

weber silicone N has been developed for durable elastic sealing of joints exposed to moisture (sanitary applications), sealing baths, hand basins, sinks and other sanitary facilities and other water supply equipment. It has a good adhesion on many building and construction elements made of concrete, glass and stainless steel material.

weber silicone N can be used for inside and outside.

CHARACTERISTICS

PROPERTIES	TYPICAL VALUES
Base	Neutral
Colors	Transparent (other colors available upon request)
Odor	Low odor
Density	0.95 g/ml
Skin formation time	5 min
Curing rate	2-3 mm/24h
Shore "A" hardness (at 7 days)	18 ± 2
Elongation at Break	500% ± 50%
Tensile modulus	0.6 MPa
Application temperature	+5°C to +40°C

INSTRUCTIONS FOR USE

SURFACE PREPARATION

All surfaces should be clean, dry, and free from grease, oil, dust and any contaminants that could harm bonding. Surfaces best to be degreased with acetone or ethanol (glass, glaze, metal) and detergent (synthetic materials). To avoid dirtiness around the gap you can use adhesive tapes.

PRODUCT APPLICATION

Cut off the top of the threaded adapter. Screw the nozzle tip on and cut off at a 45° angle, with the diameter equal to the gap width. Squeeze **weber silicone N** by mechanical or pneumatic gun. After application, the sealant should be smoothed immediately with a spatula soaked in soapy water.



PACKAGING

Leb	Syria	Jordan	UAE	Qatar	Kuwait	KSA	Oman
300 g	-	-	-	-	-	-	-

The sealant bead should not be wider than 25 mm and the minimum joint width should be 6 mm to allow in the construction field proper application and tooling of sealant. The ideal ratio of joint width to depth is 2:1.

For proper design deep joints should be filled with back-up rod. If joints are too shallow to allow backing material to be used, we recommend use of adhesive tape. This acts as a back-up rod to prevent seal in forming of three-sided adhesion and allows proper work with the joint.

Remove masking tape before skin formation. Joint should be allowed to fully cure and should not be painted.

RECOMMENDATION

Do not apply **weber silicone N** on wet surfaces and in totally confined spaces because it requires atmospheric moisture to cure.

weber silicone N is not intended for sealing joints of natural stone (granite, sandstone, marble...) or for applications involving structural glazing (aquarium and terrariums)

Do not apply **weber silicone N** on sensitive metal surface (coppers and silver steel of mirrors)

Do not use **weber silicone N** on bituminous substrates, substrates based on natural rubber, chloroprene or EPDM, PE, PP or on building materials and flexible plastics which might bleed oils, plasticizers or solvents.

STORAGE

12 months from production date, in original unopened packaging and protected from humidity.

Store in a well - ventilated room and at temperatures between +5°C and +27°C.

The containers must be protected from direct sunlight.

SAFETY PRECAUTIONS

Application should be done in a ventilated area away from any heat source. Wear protective gear for hands and eyes and avoid breathing of vapor. If mixed resin comes into contact with the skin, it should be promptly removed before hardening with paper towel. After curing, remove from hands with water and soap. In case of heavy vapor inhalation, place affected person in an open-air area. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting. In all cases, seek medical attention. In case of fire, use CO2 foam to extinguish. Tightly seal containers when not in use, store them away from heat and carefully dispose empty ones.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

NOTE

The information included on this Technical Data Sheet is the sole property of SODAMCO Holding. The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.