





weberjoint perfect

High performance, low stain, cementitious tile grout with hydro repell® and mould stop® technologies

Tile Fixing

| Leb | Egypt | Jordan | UAE | Qatar | Kuwait | KSA | Oman |
|-----|-------|--------|-----|-------|--------|-----|------|
| 5kg | 5kg | 5kg | 5kg | 5kg | 5kg | 5kg | 5kg |

PRODUCT

weberjoint perfect is a high performance cement-based ready to mix tile grout, classified as CG2WA, used for filling grout, used for filling tile joints in wet and dry areas.

Specific attributes:

- Highly stain resistant (even coffee, wine, ketchup, etc...)
- Anti-fungus with MOULD STOP Technology
- Highly water resistant with HYDRO REPELL technology
- Anti-cracks (joints between 1.5 and 20 mm width)
- High abrasion resistance

weberjoint perfect is easy to apply and can be cleaned easily. It only needs to be mixed with water and have good adhesion to tile's sides. weberjoint perfect is available in a wide range of attractive colors (please consult our color chart board).

SCOPE OF USE

weberjoint perfect is suitable to fill joints from 1.5 to 20 mm width, between ceramic tiles, marble and natural stones, glass mosaics, earthenware (faience), porcelain, terracotta,

weberjoint perfect can be used for internal and external applications, including:

Swimming-pools

- **Balconies**
- Terrace
- Wet areas Bathrooms, kitchens

Expansion joints in walls and floors should be filled with an appropriate sealant like weber jointseal PU or weber seal PS 1000 PG/GG.

| CHARACTERISTICS | | | | | |
|-----------------------------|---|--|--|--|--|
| Mixing water | 1.15 to 1.25 L./ 5 kg bag | | | | |
| Fresh density @23°C | 1.9 ±0.05 | | | | |
| Color | wide range of colors, special colors can be done upon request | | | | |
| Pot Life | 45 min. | | | | |
| Setting time (min) at 23°C | 45 min. | | | | |
| Service Temperature | -20°C to +70°C | | | | |
| VOC as per US EPA method 24 | None (< 5g/LT) | | | | |

APPLICABLE STANDARDS

ISO 13007

ANSI A118.7 (polymer modified cement grouts) Classification according to EN 13888: CG2 WA



| TEST RESULTS | | | | | | | |
|--|-----------|--|--|--|--|--|--|
| Test results as per EN 13888:2009 | Results | Standards requirements for type CG class 2WA | | | | | |
| Flexural Strength as Per EN 12808-3:2002 (N/mm²) | 6 N/mm² | >3.5 N/mm² | | | | | |
| Compressive Strength as per EN 12808-3:2002 | >15 N/mm² | >15 N/mm² | | | | | |
| Water Absorption after 30 min as per EN 12808-5 | 0.1 g | < 2 g | | | | | |
| Water Absorption after 240 min as per EN 12808-5 | 0.25 g | < 5 g | | | | | |
| Shrinkage as per DIN EN 12808-4 at 28 days standard conditions | 1.38 mm/m | < 3 mm/m | | | | | |
| Abrasion Resistance as per EN 12808-2:2002 (mm³) | ≤1000mm³ | ≤1000mm³ | | | | | |

INSTRUCTIONS FOR USE

PRECAUTIONS

Before grouting with weberjoint perfect, make sure that the adhesive has completely dried; it will depend on site and weather conditions.

- 24 hours minimum after standard tile adhesives application (webercol flex, webercol plus, webercol fix, etc...).
- 4 hours minimum after fast-setting tile adhesives application (webercol fast, webercol F1, webercol flex FS).
- 14 days minimum after tiling with traditional «site-mix» mortar on floors (minimum 3 days for walls).
- Some tiles with a matt or porous texture are prone to surface staining when coloured grouts are used. It is recommended to check that no stain will occur by testing on small surface before starting the whole job.

SURFACE PREPARATION

The grooves between all external and internal ceramic surfaces to be grouted must be sound and thoroughly cleaned before the application of the product. All traces of oil or grease must be removed. All loose particles of mortar or tile adhesive in the groove must be physically removed. Joints should be emptied to at least 2/3 of the tile thickness. Before grouting make sure that tiles are set and that the adhesive had completely dried. joints width should be from 1.5mm to 20mm.

PRODUCT PREPARATION

Mix 5 kg of weberjoint perfect with 1.15 to 1.25 Lit. of clean cool water by adding the powder over the water gradually. The amount of mixing water must be respected to avoid efflorescence over the surface of the grout. An electric mixer with low rotation speed (<300 rpm) should be used. Mix for about 3 to 5 minutes until a uniform lump free paste is obtained. Let the paste rest for a few minutes before starting the application.

PRODUCT APPLICATION

Apply weberjoint perfect with a rubber spatula into the joints diagonally by filling all the gaps, make sure that the product is well compacted with no voids. Use the product within a maximum of 45 min (depending on temperature) after mixing. Avoid grouting in hot (mid-day under direct sun light) or windy or too dry environments, it is rather advised to grout in the morning or afternoon hours during the Summer season.

Cleaning of joint surfaces

Allow the grout to dry (10 or 20 minutes depending on the weather condition) before starting the cleaning process, remove surplus with a damp sponge moving diagonally to prevent removal of grout within the joints. Rinse the sponge frequently using two water containers, one to remove the grouts residue and the other one to clean the sponge. Avoid excess of water while cleaning to prevent discoloration of joints. When dry, polish the tiles with a clean, dry cloth.

Do not spray water under high pressure and avoid using any chemical cleaning agent on the grout until 3 days after the application.

CURING

When grouting in hot or windy or dry weather conditions which may persist for the coming days, it is advisable to cure the joints by lightly dampening them with clean water.

the second day after grouting, making sure not to contaminate or stain the grouted joints in the process.

RECOMMENDATION

In external application, protect the worked area from rain and freezing for 72 hours.

In internal application avoid water immersion for 72 hours.

CLEANING

Clean the tools with water after use. Cured materials can only be removed mechanically.

CONSUMPTION

Examples of consumption (in kg/m²)

| Tile size (cm) / Joint width (mm) | 2 | 4 | 6 | 10 |
|-----------------------------------|------|------|------|------|
| 2.5x2.5* | 2.30 | - | - | - |
| 15x15 | 0.38 | 0.77 | 1.15 | 1.92 |
| 30x30 | 0.19 | 0.38 | 0.58 | 0.96 |
| 60x60 | 0.10 | 0.19 | 0.29 | 0.48 |

Indicative consumptions calculated with a tile thickness of 8mm.

* In the case of mosaics with a size of 2.5 x 2.5 cm, the tile thickness of 5mm was used to calculate the consumption.

These values only give an indication about the grout



consumption.

The real product consumption can differ depending on site conditions and wastage when grouting.

This formula does not include application wastage.

TILE GROUT CONSUMPTION FORMULA:

 $C = 0.18 \times E \times H \times [(L + W) / (L \times W)]$

C: Consumption (kg/m²) E: Joint Width (mm) H: Tile Thickness (mm) L: Tile Length (cm) W: Tile Width (cm)

STORAGE

weberjoint perfect can be stored for 2 years in its original packaging, stored away from extreme temperatures and in dry conditions.

SAFETY PRECAUTIONS

The product contains cement powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated area, and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning thoroughly with soap and water. In case of contact with eyes, wash thoroughly with clean water and seek medical attention. If swallowed, do not induce vomiting and seek medical attention. The product is non-flammable.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company are listed for guidance only. For more information, please contact the company's office in your location.

NOTE

The information included on this Technical Data Sheet is the sole property of Saint-Gobain Middle East Holding SAL (previously SODAMCO Holding). The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.

