



webercol plus

High performance
cementitious tile adhesive
(Latex modified)

Tile Fixing

Leb	Egypt	Jordan	UAE	Qatar	Kuwait	KSA	Oman
-	-	20kg	25kg	25kg	25kg	20kg	25kg

PRODUCT

webercol plus is a ready mix cement-based high performance polymer "latex" modified tile adhesive for inter-nal and external use. **webercol plus** has a strong bonding effect, used for adhering large tiles, or in cases of permanent exposure to high degrees of humidity. It can be used in a damp environment, and is water resistant.

webercol plus is classified as C2TE according to EN12004. **webercol plus** is non-sagging and slip resistance «T» with ability to perform in extended open time conditions «E».

webercol plus can be «S1» deformable when mixed with weberad 225 MB. (see instruction for use).

SCOPE OF USE

webercol plus is used for fixing a wide range of tiles (ceramic, sandstone, granite, marble, porcelain, etc.) on the following substrates:

- Concrete
- Lightweight blocks
- Stone walls (cleaned and prepared)
- Existing tiles (internal use after preparation)
- Cementitious plaster and renders
- Gypsum Board (firmly fixed & dust free)
- Fixing of Polystyrene board to concrete or cementitious substrate.

Over difficult substrates such as cement board, gypsum, wood... Primer is required; **webercol prime**, consult company for advice. **webercol plus** can be used for tiling in:

- Private swimming-pools ($\leq 80m^3$).
- Bathrooms
- Stairs
- Facades
- Rooms
- Parking

CHARACTERISTICS

Appearance	Powder
Composition	Cement, siliceous sand and additives
Color	Grey or white
Paste density	1.55 ± 0.1
Open time	30 min. (EN 12004)
Pot life	2 hrs @ 20°C
Wetting capability at 10 min	90%
Shelf Life	12 months
Mixing Ratio	5 to 6lit. per 25kg 4 to 4.8lit. per 20kg
Coverage	3 to 7 kg/m ²
Service temperature	-20°C to +70°C

Total Volatile Organic Compounds (VOC)	None (<5g/l) - (EPA Method 24)
--	--------------------------------

TEST RESULTS

Test for EN 12004:2007

Open Time by Tensile Adhesion acc. EN 1346:2007 (N/mm ²)	5 minutes	1.2
	30 minutes	0.56
Tensile Adhesion Strength acc. EN 1348:2007 (N/mm ²)	Con A	1.1
	Con B	1
	Con C	1
	Con D	1

* Con A - 28 days standard conditions

* Con B - 7 days standard condition + 21 days water immersion

* Con C - 14 days standard condition + 14 days at 70°C

* Con D - 7 days standard condition, 21 days water immersion, 25 freeze/Thaw cycles

* Standard Condition - (50±5)% Relative Humidity & 23 (±2)°C

Test for AINSI A118.4: 2012

Shear strength (N/mm ²) conditions F-7.3.2 & F-7.3.3	7 days standard conditions	1.4
	28 days standard conditions	1.9

* (Above values have a ± 10% tolerance)

APPLICABLE STANDARDS

BS 5980

EN 12004, ANSI A118.4

ISO 13007

EN 12002

INSTRUCTIONS FOR USE

SURFACE PREPARATION

Surface must be clean and free from greasy matters or dust. Substrate should have been sufficiently cured in a way that any shrinkage has already occurred. Moisten slightly the substrate if it is dry at the time of application, never moisten the tiles.

PRODUCT PREPARATION

Mix **webercol plus** in the proportion of 5 to 6 liters (4 to 4.8 L. for 20kg) of clean cool water per 25 kg bag. An electric mixer with low rotation speed (< 300 rpm) can be used. Mix until a uniform lump free paste is obtained. Let the paste rest for a few minutes before starting the application.

PRODUCT APPLICATION

Apply **webercol plus**, evenly on the substrate. Use a notched trowel to have a uniform thickness. Apply the tiles on the substrate and press them firmly, while making sure that the paste does not slip from the tile sides keeping a minimum

thickness of 2 to 3 mm.

webercol plus can also be applied on the back of tiles to ensure full adhesion with all the surface. In case exceptional performance is required and for deformability with «S1» classification, each bag of 25kg **webercol plus** should be mixed with 1 liter **weberad 225 MB** (styrene butadiene latex bonding agent) + 4.4 liters clean water.

CLEANING

Clean the tools with water after use. Cured materials can only be removed mechanically.

PRECAUTIONS

Apply **webercol plus**, on the substrate by areas of around 1 m² each, which can be tiled within a maximum of 30 minutes from application time at 20°C. After that time, an outer skin may form thus preventing the tile from adhering properly to **webercol plus**.

Adjustments to the tiles should only be made during **webercol plus** open time. It is recommended to leave a minimum width of 2 mm around the tiles.

Grouting the tile joints should only be done at least 24 hours after tiling, using **weberjoint perfect**, **weberjoint** or others.

STORAGE

12 months after manufacturing date in original and non-open packaging, under cover, in dry condition, away from humidity, protected from extreme temperatures and direct sunlight.

SAFETY PRECAUTIONS

The product contains cement powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated area, and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting, in both cases seek medical attention. The product is non-flammable.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company are listed for guidance only. For more information, please contact the company's office in your location.

NOTE

The information included on this Technical Data Sheet is the sole property of Saint-Gobain Middle East Holding SAL (previously SODAMCO Holding). The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this datasheet or any information it contains, is prohibited and subject to legal pursuit.