



# webertec grout P (QATAR)

Cementitious non-shrink  
precision grout

*Technical and  
repair mortars*

Leb	Jordan	Egypt	UAE	Qatar	Kuwait	KSA	Oman
-	-	-	-	25kg	-	-	-

## PRODUCT

**webertec grout P** is a ready-to-use free flow precision grout made of sand, special cement and additives to achieve an easy handling and high performances with no bleed and highly compensated shrinkage.

## SCOPE OF USE

- Concrete jacketing for slabs, columns, beams and footings
- Void filling applications
- Filling of shutter tie rod openings
- Jointing and bedding of precast elements
- Jointing of formwork
- Concrete surface reprofiling

## ADVANTAGES

- Highly fluid
- Chloride and hydrogen free
- High early mechanical resistance
- Good resistance to chlorides and sulfates
- Easy application
- Excellent resistant to vibration and shock loads
- Pumpable

## CHARACTERISTICS

Appearance	Grey powder
Grain size	0 to 1 mm
Wet density (kg/m <sup>3</sup> )	2.15 - 2.25
Mixing water	17% - 18%
Initial Setting time (min)	255
Final Setting time (min)	325
Free from chlorides and metallic particles	

## Compressive strength (N/mm<sup>2</sup>) - STANDARD

Age	Result at 25°C
1 day	>27 BS EN 12390-3
7 days	>50 BS EN 12390-3
28 days	>60 BS EN 12390-3

## Flexural strength (N/mm<sup>2</sup>) - BS EN 196-1\*

Age	Result at 25°C
7 days	8
28 days	>10

*\*Results obtained at fluid consistency under lab conditions at 25°C ± 2: 17% water or 4.25 lit. per 25 kg bag.\*Properties listed above are only based on controlled laboratory samples and tests: Results may differ based upon statistical variations*

depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

## APPLICABLE STANDARDS

BS EN 12390-3  
BS EN 196-1

## INSTRUCTIONS FOR USE

### PRODUCT PREPARATION

The mortar or grout is obtained by mixing 25kg of **webertec grout P** with 4.25 to 4.5 lit of water. Add the powder gradually to the water and mix for 3 minutes. To ensure a homogeneous and uniform mix, an electric mixer must be used. Do not mix with other hydraulic binders. The use of additives is absolutely prohibited. Ideal application temperature is between + 5°C and + 35°C. If the application temperature is higher than 35°C, make sure to use cool water to keep the mixed grout temperature below 30°C.

CONSISTENCY	webertec grout P	WATER	3/8 AGGREGATES	VOLUME IN PLACE
FLUID	25kg	4.25 to 4.5L	0	13L
PLASTIC	25kg	3.5 to 3.75L	0	13L
MICRO-CONCRETE	25kg	3.75 to 3.87L	10kg	17L

### PRODUCT APPLICATION

Clean the concrete substrate or the area between the forms. Pour **webertec grout P** continuously, in one direction to avoid air pockets. The maximum grouting thickness per layer is 6 cm. **webertec grout P** can be used for jacketing. Existing surface needs to be roughened and cleaned. For bedding of precast panels, build a solid leak-proof formwork, saturate the concrete substrate with water for at least few hours prior to pouring and remove all residual water.

## CURING

Once the grout starts to set, it should be cured either by a curing compound like ad cure Y 20 or ad cure WH or by covering with properly sealed plastic sheeting. If the configuration and the tightness of the forms allow by pouring 1 to 2 cm of cool water over the surface and maintaining it until the striking of the forms.

## YIELD

12.5 to 14 liter per 25 kg bag depending on consistency.

## STORAGE

12 months after manufacturing date in original and non-open packaging, under cover, in dry condition, away from humidity, protected from extreme temperatures and direct sunlight.

## SAFETY PRECAUTIONS

The product contains cement powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated area,

and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning thoroughly with soap and water. In case of contact with eyes, wash thoroughly with clean water and seek medical attention. If swallowed, do not induce vomiting and seek medical attention. The product is non-flammable.

## DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

## NOTE

The information included on this Technical Data Sheet is the sole property of Saint-Gobain Middle East Holding SAL (previously SODAMCO Holding). The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this datasheet or any information it contains, is prohibited and subject to legal pursuit.