



webercol premium F (KSA)

Two components high performance rapid setting highly flexible tile adhesive (Latex modified)

Tile Fixing

Leb	Egypt	Jordan	UAE	Qatar	Kuwait	KSA	Oman
-	-	-	-	-	-	20kg+4.8L	-

PRODUCT

webercol premium F is a two-component cement-based polymer modified, flexible, rapid setting, waterproof... tile adhesive for internal & external use.

webercol premium F is a rapid setting tile adhesive that maintains superior workability and bonding strength especially formulated for use with thin and large format tiles. **col premium F** exceeds standard requirements EN12004 and is classified as C2TES1.

webercol premium F is S1 deformable according to standard EN 12002 with ability to perform in extended open time conditions «E».

The particular flexibility of **webercol premium F** along with a high mortar transformation capability will insure durable bonding in internal and external environments with a wide range of tiles and where exposure to thermal and dimensional variations are expected.

SCOPE OF USE

Applicable tile types include:

- Thin and large format tile
- Agglomerated tiles (composite tiles)
- Full body & vitrified porcelain tiles (glazed or unglazed)
- Ceramic
- Granite

- Marble
- Sandstone
- Mosaics

Applicable substrates include:

- Concrete
- Lightweight blocks
- Stone walls (cleaned and prepared)
- Cement-based plaster and renders
- Gypsum boards
- Wood agglomerates
- Over existing tiles (after preparation)
- Cement Boards (Priming with **webercol prime**)

Over difficult substrates such as gypsum, wood..., primer is required, consult company for advice.

Applicable conditions include:

- Where thermal and dimensional variations are expected
- In vibrating areas
- For external & internal waterproof tiling
- Where resistance to chemical aggression is required

Applicable cases include:

- Heated floors
- Terraces
- Swimming pools
- Facades
- Bathrooms
- Rooms
- Stairs

- Parking
- Balconies
- Public showers
- Hospitals
- Subways

CHARACTERISTICS

Appearance	Powder + Liquid
Powder composition	Cement (ASTM C150), fillers-sand and admixtures
Liquid composition	Resins (polymer additives) and admixtures
Color	Grey or White
Density	1.52 kg/lit.±0.05
Open Time	30 min. at 20°C
Pot Life	1 hour at 20°C
Setting Time (hours)	Initial set: ±4h Final set: 5h to 6h
Drying time before traffic	24 hours at 20°C
Shelf Life	6 months
Mixing Ratio	Mix pre-packed liquid with powder
Individual VOC: <Limit	Pass (Test done as per CPDH Method 01350)
TVOC: <0.01 mg/m ³	Pass (Test done as per CPDH Method 01350)
Coverage	Notched trowel 6 by 6mm = ±3 kg/m ² 8 by 8mm = ±5Kg/m ²
Service Temperature	-20°C to +70°C

TEST RESULTS

Test for EN 12004:2007

Open Time by Tensile Adhesion acc. EN 1346:2007 (N/mm ²)	20 minutes	1
	30 minutes	0.9
Tensile Adhesion Strength acc. EN 1348:2007 (N/mm ²)	Con A	≥1.9
	Con B	≥1
	Con C	≥1.4
	Con D	≥1.4

* (Above values have a ±10% tolerance)

* Con A - 28 days standard conditions

* Con B - 7 days standard condition +21 days water immersion

* Con C - 14 days standard condition +14 days at 70°C

* Con D - 7 days standard condition, 21 days water immersion, 25 freeze/Thaw cycles

* Standard Condition - (50±5)% Relative Humidity & 23(±2)°C

TEST FOR EN 12002

Deformation from horizontal plane (mm)±2.5

APPLICABLE STANDARDS

EN 12004:2007

ISO 13007-1 :2007

INSTRUCTIONS FOR USE

SURFACE PREPARATION

Surface must be clean, sound, and free from greasy matters and dust. Substrate should have been sufficiently cured in a way that any shrinkage has already occurred. Moisten slightly the substrate if it is dry at the time of application, never moisten the tiles.

PRODUCT PREPARATION

Mix the two components of **webercol premium F** by pouring the powder in the liquid progressively while stirring the liquid. An electric mixer with low rotation speed (<300 rpm) can be used. Mix until a uniform lump free paste is obtained. Let the paste rest for a few minutes before starting the application.

PRODUCT APPLICATION

Apply **webercol premium F** evenly on the substrate. Use a notched trowel to have a uniform thickness of 2 to 3mm minimum. Apply the tiles on the substrate and press them firmly, while making sure that the paste does not slip from the tile sides. **webercol premium F** can also be applied on the back of tiles to ensure full adhesion on the entire surface.

CLEANING

Clean the tools with water after use. Cured materials can only be removed mechanically.

PRECAUTIONS

Apply **webercol premium F** on the substrate by areas of around 1m² each, which can be tiled within a maximum of 30 minutes from application time at 20°C. After that time, an outer skin may form thus preventing the tile from adhering properly to **webercol premium F**. Adjustments to the tiles should only be made during **webercol premium F**'s open time. It is recommended to leave a minimum width of 2mm around the tiles. Grouting the tile joints should only be done at least 24 hours after tiling, using **weberjoint perfect**, **weberjoint protect**, **weberexox easy**, **weberjoint deco** or **weberjoint**.

For immersed areas, allow 21 days curing for **webercol premium F** before filling with water.

Clean the tools with water after use.

STORAGE

webercol premium F can be stored for 6 months in dry conditions, away from extreme temperatures and protected against wind.

SAFETY PRECAUTIONS

The product contains cement powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated area, and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning thoroughly with soap and water. In case of contact with eyes, wash thoroughly with clean water and seek medical attention. If swallowed, do not

induce vomiting and seek medical attention. The product is non-flammable.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

NOTE

The information included on this Technical Data Sheet is the sole property of Saint-Gobain Middle East Holding SAL (previously SODAMCO Holding). The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this datasheet or any information it contains, is prohibited and subject to legal pursuit.