



# weberpremix SP-33 (KSA)

One coat high bonding ready mix plaster for light weight blocks

*Plastering  
Mortars*

| Leb | Egypt | Jordan | UAE | Qatar | Kuwait | KSA  | Oman |
|-----|-------|--------|-----|-------|--------|------|------|
| -   | -     | -      | -   | -     | -      | 50kg | -    |

## PRODUCT

**weberpremix SP-33** is a fiber reinforced cement-lime ready mix plaster used for traditional plastering works in a clean and speedy manner, while keeping a homogeneous mix. Due to its high content in fibers and additives, it allows better shrinkage control as well as improved workability, curing and impermeability. **weberpremix SP-33** is a special product dedicated for light weight blocks (Autoclaved Aerated Concrete Blocks) that can be applied for external and internal plastering without any rush coat. It can also be used for normal masonry blocks without rush coat. **weberpremix SP-33** can be applied on concrete provided that a suitable rush coat is applied before (**weberpremix SRC-2** or **weberpremix SRC-S**). **weberpremix SP-33** can be applied traditionally by hand or by using modern plaster-spraying machines. It should not be used on painted surfaces or floors.

**weberpremix SP-33** includes all the features of the **weberpremix SP-11**, that makes it a perfect solution for all substrates.

## CHARACTERISTICS

|  |  |
|--|--|
| Color  | Grey   |
| Composition  | Portland cement, selected sand, fibers and other additives including powder polymers |
| Grain size   | Up to 3mm  |
| Mixing ratio                                       | 7-9 liters per 50kg bag  |
| Fresh density                                      | 1.60±0.10  |
| Wet mix life                                       | <2 hours @20°C   |
| Compressive strength at 28 days - EN 1504 -11      | 3.5 - 7.5 Mpa<br>Class CS III as per EN 998  |
| Adhesion strength test at 28 days<br>BS EN 1015-12 | >0.3Mpa  |

## APPLICABLE STANDARDS

BS 4551: Part 2  
ASTM C 150  
ASTM C 926  
ASTM C 897  
EN 13914-1  
EN 13914-2  
BS EN 1015-12

## INSTRUCTIONS FOR USE

### SUBSTRATE PREPARATION

The substrate must be clean, sound, and free from dust and all traces of oil and laitance. Although **weberpremix SP-33** can be applied directly over light weight block, Smooth concrete surfaces, or those with low absorption, can be made more receptive to plaster application by first applying a spatter dash slurry coat (**weberpremix SRC-2** or **weberpremix SRC-S**) as a key coat for improved bonding & adhesion of subsequent layers. A few hours before the application of **weberpremix SP-33**, dampen the rush coat with clean water.

### PRODUCT PREPARATION

Mix manually or mechanically a 50kg bag of **weberpremix SP-33** with 7 to 9 litres of clean water until a homogeneous paste is obtained. Let the mix rest for a few minutes.

If a spraying machine is used, the mixing is carried out automatically.

### PRODUCT APPLICATION

Apply the plaster on the prepared surface by spraying it or manually with a plastering trowel at a thickness between 10 and 20mm in one layer. Finish the surface with a wooden or steel float as required. Let the product set properly on the surface before any curing.

### CURING

Protect the newly applied plaster from sunshine and wind.

The new plaster has to be cured with water for at least three days by spraying 3 to 4 times daily.

### CONSUMPTION

Approximately 1.6kg per m<sup>2</sup> per 1mm thickness.

### STORAGE

12 months after manufacturing date in original and non-open packaging, under cover, in dry condition, away from humidity, protected from extreme temperatures and direct sunlight.

### SAFETY PRECAUTIONS

The product contains cement powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated area, and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting, in both cases seek medical attention. The product is non-flammable.

### DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

## NOTE

The information included on this Technical Data Sheet is the sole property of Saint-Gobain Middle East Holding SAL (previously SODAMCO Holding). The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.