



weberpremix key coat (Lebanon)

Ready mixed spatterdash
slurry coat

*Plastering
Mortars*

Leb	Egypt	Jordan	UAE	Qatar	Kuwait	KSA	Oman
50kg	-	-	-	-	-	-	-

DTU 26.1
DTU 20.1
DTU 23.1

PRODUCT

weberpremix key coat is a ready mixed mortar based on mineral bonding agent used for preparing cement based surfaces before rendering. It improves the adhesion of the new plaster, cement & gypsum based. It is applied on internal or external walls and ceilings, fair faced concrete, masonry blocks, and old cement based plaster.

CHARACTERISTICS	
Appearance	Brownish granular powder
Composition	Portland cement, selected sand, additives
Grain size	0 to 4mm
Resistance to fire as per BS EN 998 -1	Class A1

APPLICABLE STANDARDS

BS 5262:1991
BS 5492:1990
BS 4551:Part 2:1998
ASTM C 150
ASTM C 926
ASTM C 897

INSTRUCTIONS FOR USE

SURFACE PREPARATION

Substrates must be sound, clean, dust free and free from all traces of oil, curing compound, gypsum, paint or laitance. The support must be dampened a few hours before the application of **weberpremix key coat**.

PRODUCT PREPARATION

Mix a 50kg bag with 8 to 9 liters of clean cool water in order to obtain the consistency desired. For specific cases, when an important adhesion is required, 1kg of **weberad 240 LTX** can be added to the mixing water. Mixing has to be done with an electric mixer.

PRODUCT APPLICATION

Apply the **weberpremix key coat** using a tyrolean box or a power spray gun.

CURING

Protect the newly applied plaster from sunshine and wind. The new plaster has to be cured with water for at least three days by spraying 3 to 4 times daily.

CONSUMPTION

Between 5 to 6kg/m², depending on the substrate and the application method.

STORAGE

12 months after manufacturing date in original and non-open packaging, under cover, in dry condition, away from humidity, protected from extreme temperatures and direct sunlight.

SAFETY PRECAUTIONS

Avoid prolonged contact with skin. Wear protective gear for hands and eyes. Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting, in both cases seek medical attention. The product is non-flammable.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

NOTE

The information included on this Technical Data Sheet is the sole property of Saint-Gobain Middle East Holding SAL (previously SODAMCO Holding). The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this datasheet or any information it contains, is prohibited and subject to legal pursuit.



Lebanon, SODAMCO S.A.L. Main Road, Hosrayel (Jbeil)

EN 998-1:2016

Mortar for general purpose (GP) to exterior & interior application

Reaction to fire: Class A1

Water Absorption: W1

Water vapor permeability: μ 15/35

Thermal conductivity: 1.21 W/m.K (P = 90%)

Durability (freez/thaw): evaluation based on value assumptions or the places where the mortar is used.