



# webercol WP (Qatar)

Latex modified cement based  
tile adhesive

*Tile Fixing*

Leb	Egypt	Jordan	UAE	Qatar	Kuwait	KSA	Oman
-	-	-	-	25kg	-	-	-

## PRODUCT

**webercol WP** is a ready mix cement-based tile adhesive modified with redispersable polymer for internal walls and floor tiling as well as external flooring.

**webercol WP** is a latex-Portland cement mortar as per ISO 13007 and ANSI A118.4 and is classified as C1T according to EN 12004.

**webercol WP** has a strong bonding effect and is water resistant.

## ADVANTAGES

- Requires only addition of water on site
- Excellent slip resistance
- Suitable for internal and external applications
- Excellent adhesion on variety of tiles
- Suitable for horizontal & vertical applications

## SCOPE OF USE

**webercol WP** is used for fixing a wide range of tiles (ceramic, sandstone, etc.) on the following substrates:

- Concrete
- Lightweight and AAC blocks (primer is recommended)
- Stone walls (cleaned and prepared)
- Gypsum board
- Cementitious plasters and renders

- Cement board
  - Replace concrete by concrete and screed
- Substrate made of Gypsum plaster is not advisable.

**webercol WP** can be used for tiling in:

- Bathrooms
- Stairs
- Rooms
- Parking
- Balconies and terraces

## CHARACTERISTICS

Appearance	Powder
Composition	Cement, siliceous sand and additives
Color	Grey or white
Paste density	1.65 ± 0.1
Open time	20 min @ 20°C
Pot life	4 hrs @ 20°C
Shelf life	12 months
Mixing ratio	5-5.5lit. per 25kg
Coverage	3-7kg/m <sup>2</sup>
Thickness of application	3-10mm
Service temperature	-20°C to +70°C
Total Volatile Organic Compounds (VOC)	None (<5g/l) - (EPA Method 24)

## TEST RESULTS

### Test for EN 12004:2007

Open time by tensile adhesion acc. EN 1346:2007 (N/mm <sup>2</sup> )	20 minutes	0.56
Tensile adhesion strength acc. EN 1348:2007 (N/mm <sup>2</sup> )	Con A	>0.6
	Con B	>0.5
	Con C	>0.5
	Con D	>0.5

\* Con A - 28 days standards conditions

\* Con B - 7 days standard condition + 21 days water immersion

\* Con C - 14 days standard condition + 14 days at 70°C

\* Con D - 7 days standard condition, 21 days water immersion, 25 freeze/Thaw cycles

\* Standard Condition - (50 ± 5)% Relative Humidity & 23 (± 2)°C  
All values given are subject to 5 to 10 % tolerance.

## TEST RESULTS

### Test for ANSI A118.4

Shear strength (N/mm <sup>2</sup> ) F-7.3.2	7 days standard conditions	≥1.2
	28 days standard conditions	≥1.4

All values given are subject to 5 to 10 % tolerance.

## APPLICABLE STANDARDS

EN 12004:2007 C1T

ANSI A118.4

ISO 13007

## INSTRUCTIONS FOR USE

### SURFACE PREPARATION

Substrate must be clean and free from greasy matters or dust. It should have been sufficiently cured in a way that any shrinkage has already occurred.

Moisten slightly the substrate if it is dry at the time of application, never moisten the tiles.

### PRODUCT PREPARATION

Mix 25kg of **webercol WP** with 5-5.5lit of clean cool water. An electric mixer with low rotation speed (< 300 rpm) can be used. Mix until a uniform lump free paste is obtained. Let the paste rest for a few minutes before starting the application.

### PRODUCT APPLICATION

Apply **webercol WP** evenly on the substrate. Use a notched trowel to have a uniform thickness.

Apply the tiles on the substrate and press them firmly, while making sure that the paste does not slip from the tile sides keeping a minimum thickness of 2-3mm. **webercol WP** can also be applied on the back of tiles to ensure full adhesion on the entire surface. Clean the tools with water after use. Cured materials can only be removed mechanically.

In case exceptional performance is required, each bag of 25kg **webercol WP** should be mixed with 1lit **weberad 225 MB** + 4lit of clean water.

## PRECAUTIONS

Apply **webercol WP** on the substrate by areas of around 1m<sup>2</sup> each, which can be tiled within a maximum of 20 minutes from application at 20°C. After that time, an outer skin may form thus preventing the tile from adhering properly to **webercol WP**. Adjustments to the tiles should only be made during **webercol WP**'s open time.

It is recommended to leave a minimum width of 2mm around the tiles (or as designed).

Grouting the tile joints should only be done at least 24 hours after tiling, using **weberjoint perfect**, **weberjoint** or **weberjoint deco**.

## STORAGE

12 months after manufacturing date in original and non-open packaging, under cover, in dry condition, away from humidity, protected from extreme temperatures and direct sunlight.

## SAFETY PRECAUTIONS

The product contains cement powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated area, and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting, in both cases seek medical attention. The product is non-flammable.

## DISCLAIMER

While the company guarantees its products against defectivematerials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company are listed for guidance only. For more information, please contact the company's office in your location.

## NOTE

The information included on this Technical Data Sheet is the sole property of Saint-Gobain Middle East Holding SAL (previously SODAMCO Holding). The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this datasheet or any information it contains, is prohibited and subject to legal pursuit.