



# Biflex PL anti-root 4MM/200

SBS modified bituminous  
membrane for roof gardens

*Waterproofing*

Leb	Egypt	Jordan	UAE	Qatar	Kuwait	KSA	Oman
1x10m	1x10m	1x10m	1x10m	1x10m	1x10m	1x10m	1x10m

## GENERAL

A high performance elastomeric waterproofing membrane which combines the ability to withstand high ambient temperature with the usual characteristics of an SBS membrane of high flexibility at low temperature that makes it easy to apply at sub-zero temperature.

The SBS Bitumen Compound is carefully blended with high quality anti-root additives that makes it suitable for all types of waterproofing works especially roofs gardens, flower boxes and underground backfilled structures.

## SPECIAL FEATURES

- Positive vapor barrier
- Excellent resistance to atmospheric agents
- High flexibility during application at sub-zero temperature with no physical strains
- High malleability making it entirely suitable for difficult basement and foundation works.
- High softening point allowing it to maintain shape stability at high temperatures.
- Withstand thermal shocks
- Accommodates structural movements
- Resistant to chemical attacks

## SIZE AND SURFACE FINISH

Biflex PL anti-root 4mm/200 is available in 1m wide and 1m length. The top surface finished with polyethylene film.

## REINFORCEMENT CORE AND COATING MIXTURE

Biflex PL anti-root 4mm/200 waterproofing membranes is reinforced with 200g/m<sup>2</sup> non woven spunbond polyester reinforcement that gives the membrane dimensional stability and resistance to puncture. It is coated with a specially formulated mixture of SBS modified bitumen and anti-root additive which makes the membrane resistant to water, atmospheric agents, and plantations roots and malleable at low temperature while retaining a high softening point.

## INSTRUCTIONS FOR USE

The membrane must first be unrolled and laid down on the area to which it is to be applied. Check the orientation carefully. Adjacent rolls should then be laid, each overlapping the one next to it by 10cm on the side and 15cm at the ends. Taking care not to change the orientation of each roll, reverse the process until each has been re-rolled. When laying the roll, the lower surface should be heated with a propane torch, using sweeping left to right movements. This will melt the lower surface of the membrane and allow it to stick to the substrate. Continue this process for each subsequent roll, remembering that the overlaps must be 10cm for the edges and 15cm at the ends. When the process is complete, carry out an inspection to ensure total adhesion. When applied in a totally bonded system, a coat of **weberdry prime WB** or **weberdry prime SB** should be applied at the rate of 200-300g/m<sup>2</sup>.

Properties	Typical Values	Test method
Reinforcement	200g/m <sup>2</sup>	ASTM D 5147
Cold flexibility	-5°C	ASTM D 5147
Maximum tensile force* (23 ± 2°C) Longitudinal Transversal	900N/5cm (18KN/m) 600N/5cm (12KN/m)	UEAtc 2001 (ASTM D 5147)
Elongation* Longitudinal Transversal	50% 50%	ASTM D 5147/UEAtc 2001
Shear resistance of joints* Longitudinal Transversal	850N/5cm 500N/5cm	UEAtc 2001
Tear strength* Longitudinal Transversal	600N 450N	ASTM D 4073
Softening point	150-160°C	ASTM D36
Penetration (@25°C)	15-25dmm	ASTM D5
Puncture resistance To Static load To impact	L25 I10	UEAtc 2001 UEAtc 2001
Resistance to puncture	1000N	ASTM E 154
Water absorption (24 hours @23±2°C)	<1%	ASTM D 5147
Biflex membranes are resistant to chlorides, sulphates and phosphates found in ground water.		

\* Values subject to a variation of ±20% (Except for Resistance to puncture ±10%)

## STORAGE

The membranes shall be in its original closed packaging pallets and protected from all sources of heat and extreme temperatures. Do not stack pallets on top of each other. Do not store pallets direct in the sun or in humid area, this may lead to damage its physical properties and reduces its shelf life.

The shelf life is 12 months from date of production if stored as per recommendations.

## DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

## NOTE

The information included on this Technical Data Sheet is the sole property of Saint-Gobain Middle East Holding SAL (previously SODAMCO Holding). The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.