



weberbloc fix LW (KSA)

Polymer modified mounting mortar and glue for light weight & AAC blocks

*Plastering
Mortars*

Leb	Egypt	Jordan	UAE	Qatar	Kuwait	KSA	Oman
-	-	-	-	-	-	50kg	-

PRODUCT

weberbloc fix LW is a premix mortar and adhesive used to fix light weight block that requires only the addition of water. It is made of cement, graded sand and additives for improved workability, bonding and water retention.

weberbloc fix LW is particularly adapted for mounting light weight blocks.

Features

- Easy to use
- No curing required after block fixing
- Long pot life
- Strong adhesion
- Optimum compressive strength

Substrates

- AAC blocks
- Light weight masonry blocks
- Concrete Hollow blocks

CHARACTERISTICS

Color	Grey/White
Composition	Cement, graded sand, additives

Appearance	Powder
Mix Density	1.6±0.1
Grain size	maximum 1mm
Pull off strength at 28 days (EN 12004-2)	>1MPa
Pot life	3 hours (at 21°C)
Hard dry	24 hours

INSTRUCTIONS FOR USE

SURFACE PREPARATION

The substrate must be clean, sound, and free from dust and all traces of oil and laitance. It must not be over heated nor frozen. In hot weather, the surface receiving **weberbloc fix LW** should be brushed with some water immediately prior to application.

PRODUCT PREPARATION

Mix a 50kg bag of **weberbloc fix LW** with 11 to 12 liters of potable cool water. Mixing has to be done with a mechanical mixer.

PRODUCT APPLICATION

Apply **weberbloc fix LW** to the light weight blocks using a notched trowel to approximately 3 to 5mm thickness. Place the blocks onto the mortar ensuring good contact. Check the level and continue with the next block. Remove excess material with a wet sponge before setting. Care should be taken in order not to mount blocks if a dry skin has already formed on the freshly-

applied mortar. Ideal application temperature is between +5°C and +35°C.

CURING

Protect the newly applied material from sunshine and wind. In hot weather it is advisable to cure the new material with water.

YIELD

1000Kg of **weberbloc fix LW** plus approximately 23% of clean cool water will give between 740-760 liters of workable mortar. A 50Kg bag = approx. 38 Liters of fresh mortar.

STORAGE

12 months after manufacturing date in original and non-open packaging, under cover, in dry condition, away from humidity, protected from extreme temperatures and direct sunlight.

SAFETY PRECAUTIONS

The product contains cement powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated area, and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting in both cases seek medical attention. The product is non-flammable.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are listed for guidance only. For more information, please contact the company's office in your location.

NOTE

The information included on this Technical Data Sheet is the sole property of Saint-Gobain Middle East Holding SAL (previously SODAMCO Holding). The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.