



weberdry 116 FX Grey/White

Flexible cement based acrylic waterproof coating

Waterproofing

Leb	Egypt	Jordan	UAE	Qatar	Kuwait	KSA	Oman
15kg	-	15kg	22.5kg	15kg	22.5kg	15kg	22.5kg
-	-	-	-	-	-	30kg	-

powder (A) 10kg + 5kg liquid (B)= 15kg

powder (A) 15kg + 7.5kg liquid (B)= 22.5kg

powder (A) 20kg + 10kg liquid (B)= 30kg

PRODUCT

weberdry 116 FX Grey/White is a cement based two component polymer modified waterproofing slurry, available in grey and white.

It is applied to concrete and mortar structures to prevent water infiltration.

weberdry 116 FX must be used on damp cement based substrate and this waterproof membrane can be used under interior and exterior ceramic tiles.

SCOPE OF USE

weberdry 116 FX Grey/White is used for external and internal waterproofing, crack sealing, repair work in the following structures:

- Bathrooms commercial & residential
- Roofs and foundations
- Kitchens - Commercial & Residential
- Steam rooms, showers
- Laundry rooms

- Swimming pools
- Facades: As a damp-proof coating

It is used as well, as a backing to marble, granite stones against water absorption.

Protection and waterproofing of concrete surfaces and facades, and on top of spray polyurethane foam roof insulation. (Applied material should not be left exposed).

ADVANTAGES

- Waterproof, flexible, crack bridging
- Approved for use in contact with potable water
- Outstanding adhesion to concrete and masonry

CHARACTERISTICS	
Powder	Grey or white
Bulk density	1.5
Mix density (A+B)	1.4±0.05 (fresh mortar)
Pull off strength (BS 1881 Part 207) @28 days	0.80N/mm ²
Crack bridging ability (ASTM C 836)	No sign of crack, loss of adhesion or any other types of failure was observed
Depth of water penetration under pressure after 28 days (BS EN 12390 Part 8:2000)	NIL

Presence of water leakage on the surface of sample during test after 28 days (BS EN 12390 Part 8:2000)	NIL
--	-----

All tests were carried out @ temp 23±2°C and relative humidity of 50±55%

INSTRUCTIONS FOR USE

SURFACE PREPARATION

The substrate to be treated must be perfectly sound, clean, free from grease, oil, dust and any friable matters. Soak the surface with water, removing any excess so that the substrate is saturated but the surface is dry.

PRODUCT PREPARATION

Pour component B (liquid) into a suitable clean container, then slowly add component A (powder) while stirring with a mechanical mixer. Mix until the product is perfectly smooth and homogeneous using a low speed mechanical stirrer in order to avoid any excessive incorporation of air.

PRODUCT APPLICATION

The paste can be applied with a brush, roller or trowel. For a trowable consistency reduce the amount of component B (liquid) used. Apply first layer of **weberdry 116 FX** with sufficient thickness to plug pores, cracks and holes. Apply the second layer as soon as possible, after hardening of the first layer, to ensure proper adhesion between layers. If needed apply a third layer.

The thickness of **weberdry 116 FX** should be at least 1.5mm. In hot weather, wind or sunshine, take all necessary measures to prevent the coating from rapid water evaporation.

COVERAGE

Approx. 2 to 3kg/m² depending on the surface and consistency required (approx 1.8kg per m² for 1mm thickness).

STORAGE

Can be stored for 6 months in original package in a dry and tempered area.

SAFETY PRECAUTIONS

The product contains cement powders which, when mixed with water, release alkalis that could be harmful to the skin. It is preferable that the application be done in a ventilated area, and to wear protective gear for hands, eyes and respiratory system and to avoid breathing of the dust. Splashes on the skin should be washed away by cleaning with soap and water. In case of contact with eyes, wash thoroughly with clean water. If swallowed, do not induce vomiting, in both cases seek medical attention. The product is non-flammable.

DISCLAIMER

While the company guarantees its products against defective materials, the use and application of these products are made without guarantee since the conditions of their application are beyond its control. It is recommended to verify with the company that the product is suitable for the intended use, and that this Data Sheet version is the latest one. The company may modify it without prior notice. Technical characteristics are

listed for guidance only. For more information, please contact the company's office in your location.

NOTE

The information included on this Technical Data Sheet is the sole property of Saint-Gobain Middle East Holding SAL (Previously SODAMCO Holding SAL). The unauthorized disclosure, use, dissemination or copying (either whole or partial) of this data sheet or any information it contains, is prohibited and subject to legal pursuit.